ACCEPTED

BY JC DATE 1/5/26

TCFB35665

Mill Test Report

EN 10204-3.1
TA CHEN STAINLESS PIPE CO., LTD.
NO. 125 HSIN-TIEN 2ND ST.,
JENG-TEH, TAINAN, TAIWAN
TEL:(06)2793254 FAX:(06)2701382
COUNTRY ORIGIN:TAIWAN

Commodity : STAINLESS STEEL PLATE CUT STRIP

Customer : TA CHEN INTERNATIONAL, INC.

Shipper : TA CHEN STAINLESS PIPE CO., LTD.

Specification : ASTM A240/A240M-2024b ASTM A484-2023a
ASTM A480-2024 ASME SA240-2023/SA480-2023
ASTM A276-2024a Chem/Mech.only
ASTM A479-2021/ASME SA479-21 Chem/Mech.only
ASTM A666-10/QQS-763-F Chem only

Destination : LAKELAND

Customer's PO# : LC2176 **Certificate NO** : ZG0152001

Factory O/N : QA02Z5240 **Date** : 2025/6/23 **INVOICE NO** : QA02ZG0152

Item No.	Case No. (Crate No.)	Heat No.	Supplier	Size	Quantity Pcs	Weight Kgs	C	Si	Mn	P	S	Ni	Cr	Mo	N	Cu
							Chemical Composition in %									
							- 0.030	- 0.750	- 2.000	- 0.045	- 0.030	8.000 12.00	18.00 20.00	- 0.750	- 0.100	- 0.750
01	018,019,020.021	Y240226D47-3	TSINGSHAN	.125 X 1.000 X 144 304/304L	340	808	0.024	0.400	1.390	0.032	0.002	8.010	18.12	0.010	0.065	0.030
02	015,016	ZS066	WALSIN	.125 X 1.250 X 144 304/304L	182	527	0.027	0.380	1.380	0.024	0.002	8.000	18.06	0.010	0.068	0.030
03	024.025.026.027	Y240226D47-3	TSINGSHAN	.125 X 1.500 X 144 304/304L	218	774	0.024	0.400	1.390	0.032	0.002	8.010	18.12	0.010	0.065	0.030
04	007,008	Y250125A13C		.125 X 6.000 X 144 304/304L	36	492	0.028	0.370	1.120	0.028	0.002	8.000	18.12	0.010	0.050	0.030
05	009,010,011,012.013,014	Y230530G64-5	TSINGSHAN	.187 X 1.000 X 144 304/304L	428	1486	0.023	0.370	1.150	0.033	0.003	8.050	18.13	0.010	0.071	0.050
				Total	1204	4087										

Item No.	Tensile Test: 0.2%Yield Strength PSI	Tensile Strength PSI	Elongation %	Reduction of Area %	Hardness Test HRB	Bend Test	HT TEMP °F Quenching In Water	Dimension And Surface Condition	Melt Source
	30000 -	75000 -	L40	- 65.00	- 92.00		1900 -		
01	51700	91800	55.8	56.80	86.30	OK	1904	OK	INDONESIA
02	45100	96000	54	55.00	84.00	OK	1904	OK	INDONESIA
03	51700	91800	55.8	56.80	86.30	OK	1904	OK	INDONESIA
04	40500	99200	48	49.00	85.10	OK	1904	OK	INDONESIA
05	43200	95400	57	58.00	85.70	OK	1904	OK	INDONESIA

Remarks

1. NO WELD REPAIR PERFORMED
2. FREE OF MERCURY CONTAMINATION
3. ASTM A262 PRACTICE E : OK
4. MECHANICAL PROPERTIES ARE MEASURED FROM SHEET COIL BEFORE CUTTING.
5. NACE MR0175/ISO15156-3-15 ANNEX A : OK
6. ALL RAW MATERIALS HAS BEEN ANNEALLED BEFORE CUTTING AND DEBURRED ROLLING
7. HOT ROLLED ANNEALED AND PICKLED
8. ASTM A276/A 276M -2017 ChemMech. Only.
9. RoHS Compliance

Chemical and physical Properties comply to AMS5513L(304)/AMS5511K(304L)
We hereby certify the above statement to be true and correct every detail
TA CHEN has established a QMS according to ISO 9001, which is certified by LRQA (ISO 9001-0067066)

George Yang

Manager of Inspection Section/George Yang

Job: 089-25 PO: 40303 Line: 005 HT: Y250125A13C

This MTR contains:1 pages (Page:1)

MILL TEST REPORT **TA CHEN INTERNATIONAL, INC.** www.tachen.com

Cust#: RYEJAF Company#: RYERSON, INC. Vendor:
MTR#: TCFB/TCFB35665.pdf PO#: 4701151769 SO#: LQKYT7 Vendor#:

Item:G4L00080600 Bundle:ZG0152-008 Heatno:Y250125A13C