CERTIFICATE MATERIAL TEST REPORT

(DIN 50049.1 / EN 10204 3.1 / ISO 10474 3.1)

ISO 9001:2015

CAS METAL CO., Ltd.
32, Saenggogsandan 2-ro,
Gangseo-gu, Busan, Korea
Tel : 051-941-1127 Fax : 051-941-1128

CERTIFICATE No.	: CAS250605-01	ORDER NO.	: PO755-005068
CUSTOMER	: NORCA INDUSTRIAL LLC	PROJECT NAME	: P.O. N8150
MATERIAL	: ASTM/ASME A/SA182F51/60(2023ED)	ISSUED DATE	: JUN. 05. 2025.

Heat No.	Spec	CHEMICAL COMPOSITION (%)																Non-destructive examination ③		
		C	SI	Mn	P	S	Ni	Cr	Mo	V	Cu	Nb/Cb	Al	N				UT ⑤	N/A	-
	Min.						4.5	22.0	3.0					0.14				MT ⑤	N/A	-
	Max.	0.030	1.00	2.00	0.030	0.020	6.5	23.0	3.5					0.20				PT ⑤	N/A	-
E131792	H.A. ①	0.017	0.45	1.30	0.022	0.001	5.56	22.21	3.04					0.185				Dimension & Visual Inspection	GOOD	
	P.A. ①																			

BLANK

※ Remark

* Country of Origin : KOREA * Country of Melt & Pour : KOREA * NACE MR0175 AND MR0103

* ISO 9001 : 2015 * PED 2014 / 68 / EU. * CORROSION TESTED TO ASTM A262 PRACTICE E : No Defect

ARTICLES	Q'ty
01) B16.5 150# SO RF 1/2"	50EA
02) B16.5 150# SO RF 1"	50EA
03) B16.5 150# SO RF 1-1/2"	50EA
04) B16.5 150# SO RF 2"	20EA
05) B16.5 150# SO RF 2-1/2"	10EA
06) B16.5 150# SO RF 3"	25EA
07) B16.5 150# SO RF 4"	50EA
08) B16.5 150# SO RF 6"	25EA

MECHANICAL PROPERTIES	TENSILE TEST ④ (Ø12.5 x 50L)						Hardness Test	CHARPY IMPACT TEST(J)				BEND TEST
	Location ②	Temp.	Y.S.	T.S.	E.L.	R.A.	HBW	Temp. : 40 °F				Radius :
			N/㎟ (MPA)		%			Min. :				
Lot No.		℃	MIN. 450	MIN. 655	MIN. 25	MIN. 45	MAX 220	Avg. : 1	2	3	AVG	Angle :
CAS25-N24	T		491	686	42	63	162, 160	91	89	102	94	
Simulation P.W.H.T.	#1											
	#2											
	#3											

BLANK

Heat Treament ④										
	Normalizing	°C	HRS	Tempering	℃	HRS	Quenching	℃	HRS
	Solution	1040 °C	6.0 HRS W.C	Stablization	℃	HRS	Annealing	℃	HRS

☐ **Witnessed By**

☐ **Reviewed By**

We hereby certify that the material herein has been made and tested accordance with the above specification and also with the requirement called for by the above order.

CAS METAL Co., Ltd. QUALITY CONTROL DEPART

Manager of Quality Assurance Dep't

Notes
① - H.A. = Heat Analysis, P.A. = Product Analysis
② - location : L = Longitudinal Tr = Transverse T = Tangential R = Radial Treated S.R. = Stress Relieved
③ - Surface Condition : A.F. = As Forged R.M. = Rough Machined F.M. = Finish Machined
④ - A.C. = Air Cooled, F.C. = Furnace Cooled, W.C. = Water Cooled, O.C. = Oil Cooled
⑤ - UT = Ultrasonic Test, MT = Magnetic Test, PT = Penetrant Test

ACCEPTED

BY JL DATE 1/19/26

Job: 089-25 PO: 40301 Line: 013 HT: E131792