BRISMET
BRISTOL METALS, LLC

1001 E Waterfront Dr,
Munhall, PA 15120

MILL TEST REPORT

Lot Number
2021-09431
SALES ORDER / RLS
202244121400
CERT ID / REV
5243

SOLD TO:
ROBERT JAMES SALES - BUFFALO
PO BOX 7999
BUFFALO, NY 14225-7999

CUSTOMER P.O.	CUSTOMER PART	HEAT NO.
AU0847		P93H

DESCRIPTION: 33003000000803043120102
3" WELDED PIPE SCH 80S TP304/TP304L (UNS# S30400/S30403) A312/SA312 NSF-61

CERTIFICATION REQUIREMENTS

ENGINEERING
ASTM A312-22 ASME SA312-21

EDDY CURRENT EXAM
PASS IAW ASTM E426 USING DRILLED HOLE REFERENCE STANDARDS

HEAT TREAT
Annealed at 1900 Min. Deg F. and quenched in water or rapidly cooled by other means.

Chemical		Mechanical	
Test	**Result**	**Test**	**Result**
Carbon	.0211	Tensile	89550
Manganese	1.7110	Yield	46440
Phosphorus	.0305	Elongation	54.23
Sulfur	.0010	Hardness RB	85
Silicon	.3045		
Nickel	8.1405	Tension	Pass
Chromium	18.2405	TG Face Bend	Pass
Molybdenum	.3845		
Nitrogen	.0716		
Country of Origin	USA		

This report shall not be altered or reproduced, except in full, without the prior written approval of Bristol Metals LLC. This test report represents the actual attributes of the items furnished and all items were manufactured, sampled, inspected, and tested in full compliance with applicable specifications and your purchase order.
Certification is in accordance with EN10204:2004 type 3.1.
Chemical content is % by weight. Mechanical test results are in English units (inches and pounds).
No weld repairs have been performed on the base material.
Hardness in accordance with NACE MR0175/ISO 15156-3:2015 and MR0103-2015 and material is free of cold work to enhance mechanical properties.
Pipe/Tube has been Pickled and Passivated in accordance with ASTM A380.
Bristol Metals has a Quality Management System in place that is in compliance with ISO 9001:2015.
Bristol Metals does not add mercury or radioactive materials during any manufacturing process.
NAFTA country of origin: USA. Pipe/Tube Manufactured in the USA. Raw Material Melt: USA
FAR BAA –, DFARS BAA –, FAR TAA – Complies.

Quenched in water or rapidly cooled, at a rate sufficient to prevent re-precipitation of carbides, as demonstrable by the capability of heat treated pipes passing Practices A262, Practice E.

QF-576

ACCEPTED
BY JR DATE 1/22/26

Certification Date: 10/26/2022

Mike Mun

Quality Assurance Manager

Job: 099-25 PO: 40304 Line: 007 HT: P93H