MATERIAL TEST REPORT

WEBCO INDUSTRIES

Sold To: 8530200	Ship To: 8530200
ROBERT JAMES SALES/BUFFALO 2585 WALDEN AVENUE BUFFALO NY 14225-7999	ROBERT JAMES SALES/BUFFALO 2585 WALDEN AVENUE BUFFALO NY 14225-7999

Purchase Order: A0180W
Sales Order: 310928
Material: M063131513300 A/SA312 TP304L 1" S40
Delivery / File Nbr: 80552664

Description: ASTM A312-2024A ASME SA312-23
WELDED STAINLESS STEEL PIPE, TP304/TP304L

Test: FLATTENING TEST PASSED. REVERSE FLATTENING TEST PASSED. FLARE TEST PASSED. NDT ELECTRIC TESTED TO ASTM A999, TEST METHOD E426 USING A DRILL-HOLE REF. STD. THE HARDNESS FOR THE GRADE TP304/304L COMPLIES TO SECTION A.2.2 OF NACEMR0175/ISO-15156-3 AND NACE MR0103/ISO-17495-1 LATEST VERSION. HEAT TREATED AT MINIMUM OF 1900 DEGREES F AND RAPIDLY COOLED. PER ASTM A312 CURRENT REVISION. NO FILLER MATERIAL ADDED

Heat Number: OC545578

		%
CARBON	LDL	0.026
MANGANESE	LDL	1.270
PHOSPHORUS	LDL	0.033
SULFUR	LDL	0.002
SILICON	LDL	0.290
NICKEL	LDL	8.030
CHROMIUM	LDL	18.040

Ultimate	(PSI)	93,280 / 93,350
Yield	(PSI)	53,400 / 54,030
Elongation	(%)	66 / 67
Hardness	(HRBW)	80 / 80
ROA	(%)	
Origin of Melt		USA
Manufactured In		USA

ACCEPTED
BY AA DATE

We hereby certify that the above figures are correct as contained in the records of the company and that each batch has been manufactured, sampled, tested and inspected in accordance with the applicable specification stated above. This Document conforms to the requirements of Specification EN 10204 Inspection Document Type 3.1. Webco does not use mercury in testing or production of its stainless steel products. According to our records and to the best of Webco's knowledge, understanding and belief, this product was not contaminated during manufacture in our facilities. Fraudulent, fictitious, or false statements or entries may be prosecuted by law.

Date: 11/05/2024

CHARLIE CONN
Quality Manager
CCONN@WEBCOTUBE.COM

18256 West HWY 66
Kellyville OK 74039

Job: 089-25 PO: 40327 Line: 001 002 HT: OC545578