DAEKYUNG BEND
CO.,LTD.

INSPECTION CERTIFICATE

(EN10204 3.1)

115, Eosil-ro, Yangsan-Si,
Gyeongsangnam-Do,
Korea
TEL : 82-055-364-1800
FAX : 82-055-362-7074

Customer	(주)태양밴드	**Certificate. No.**	YR-26-07015
P.O. No.	A202610150	**Date of Issue**	2026-10-19
Hull No.(Project No.)	N/A	**Dimension & VI**	GOOD
Spec. for Material	ASTM A312 TP316L	**Spec. for Inspection**	KS B1543 STS316L-W

1. ITEM DESCRIPTION

DKB LOT No	Item No	Heat No	Description	Q'TY(P'cs)	Starting Material	NDE(Report No.)
JCQ4366	1	SD34285	R(C) S/10S 32A * 15A B.W	2	WELDED PIPE	N/A

* Heat Treatment Condition : 1040℃ Solution Annealing & Water Quenching

2. CHEMICAL COMPOSITION(%)

Heat No.	Spec	C	Si	Mn	P	S	Ni	Cr	Mo						
	Max	0.035	1.00	2.00	0.045	0.030	14.00	18.00	3.00						
	Min						10.00	16.00	2.00						
SD34285	L	0.017	0.60	1.06	0.029	0.002	10.03	16.16	2.07						

* L : Ladle Analysis

3. MECHANICAL PROPERTIES

Heat No	TENSILE TEST					HARDNESS TEST	CHARPY-V IMPACT TEST (Test Temp : ℃)									
	Unit	Y.S(0.2%)	T.S	E.L	R.A	TEST METHOD: HB	Specimen Size	Direction Position	ABSORBED ENERGY (Unit : J)				LATERAL EXPANSION (Unit : mm)			
		MPa	MPa	%	%				Min: (S)		(AVR)		Min : mm			
	Max	-	-	-	-	-			1	2	3	AVR	1	2	3	AVR
	Min	170	485	35	-	-										
SD34285	L,B	285	594	50												

* L : Longitudinal, T : Transvers, B : Base Metal, W : Weld Metal

Heat No	PMI	FLATTENING	CORROSION TEST	HYDROSTATIC TEST	FERRITE	GRAIN SIZE
SD34285	GOOD	N/A	N/A	N/A	N/A	N/A

REMARK

We certify this material has been manufactured and examined in accordance with all requirements of the specification and the results of all examination are acceptable

S. J. KIM

HEAD OF QUALITY MANAGEMENT