DAEKYUNG BEND
CO., LTD.

INSPECTION CERTIFICATE

(EN10204 3.1)

115, Eosil-ro, Yangsan-Si,
Gyeongsangnam-Do, Korea
TEL : 82-055-364-1800
FAX : 82-055-362-7074

Customer	주 태형산업	Certificate. No.	YR-26-09915-1
P.O. No.	ES261014-2869	Date of Issue	2026.07.09
Hull No.(Project No.)	N/A	Dimension & VI	GOOD
Spec. for Material	ASTM A312 TP316L	Spec. for Inspection	KS B1543 STS316L-W /B1500

1. ITEM DESCRIPTION

DKB LOT No	Item No	Heat No	Description	Q'TY	Starting Material	NDE(RESULT)
KJA0879	1	SD62415	45E(L) S/10S 25A B.W	1	WELDED PIPE	N/A
KJA0880	2	SD62415	90E(L) S/10S 25A B.W	4	WELDED PIPE	N/A
KJA0886	3	SD62415	TEE S/10S 25A B.W	2	WELDED PIPE	N/A
KJA0887	4	SD62415	TEE S/10S 25A * 20A B.W	2	WELDED PIPE	N/A
KDC0011	5	SE28856	90E(L) S/10S 20A B.W	7	WELDED PIPE	N/A
KDC0014	6	SD59218	90E(L) S/10S 40A B.W	22	WELDED PIPE	N/A

*** Heat Treatment Condition : 1050℃ Solution Annealing & Water Quenching**

2. CHEMICAL COMPOSITION(%)

Heat No.	Spec	C	Si	Mn	P	S	Ni	Cr	Mo
	Max	0.030	1.00	2.00	0.045	0.030	14.00	18.00	3.00
	Min	-	-	-	-	-	10.00	16.00	2.00
SD62415	L	0.017	0.55	1.05	0.032	0.002	10.1	16.35	2.03
SD62415	L	0.017	0.55	1.05	0.032	0.002	10.1	16.35	2.03
SD62415	L	0.017	0.55	1.05	0.032	0.002	10.1	16.35	2.03
SD62415	L	0.017	0.55	1.05	0.032	0.002	10.1	16.35	2.03
SE28856	L	0.057	0.36	1.02	0.034	0.006	8.01	18.08	0
SD59218	L	0.066	0.37	1.03	0.033	0.004	8.09	18.22	0

* L : Ladle Analysis P : Product Analysis

3. MECHANICAL PROPERTIES

Heat No	Unit	TENSILE TEST			HARDNESS TEST	CHARPY-V IMPACT TEST (Test Temp : ℃)		
		Y.S(0.2%)	T.S	E.L		ABSORBED ENERGY (Unit:J)		LATERAL EXP.
		MPa	MPa	%	HB	Min	AVR	Min (mm)
Spec Min		170	485	35	-	-	-	-
SD62415	L,B	298	622	57	-	-	-	-
SD62415	L,B	298	622	57	-	-	-	-
SD62415	L,B	298	622	57	-	-	-	-
SD62415	L,B	298	622	57	-	-	-	-
SE28856	L,B	285	657	60	-	-	-	-
SD59218	L,B	329	692	55	-	-	-	-

* L : Longitudinal, T : Transvers, B : Base Metal, W : Weld Metal

Heat No	PMI	FLATTENING	CORROSION TEST	HYDROSTATIC TEST	FERRITE	GRAIN SIZE
SD62415	GOOD	N/A	N/A	N/A	N/A	N/A
SD62415	GOOD	N/A	N/A	N/A	N/A	N/A
SD62415	GOOD	N/A	N/A	N/A	N/A	N/A
SD62415	GOOD	N/A	N/A	N/A	N/A	N/A
SE28856	GOOD	N/A	N/A	N/A	N/A	N/A
SD59218	GOOD	N/A	N/A	N/A	N/A	N/A

REMARK:

We certify this material has been manufactured and examined in accordance with
all requirements of the specification and the results of all examination are acceptable