DAEKYUNG BEND
CO., LTD.

INSPECTION CERTIFICATE

(EN10204 3.1)

115, Eosil-ro, Yangsan-Si,
Gyeongsangnam-Do, Korea
TEL : 82-055-364-1800
FAX : 82-055-362-7074

Customer	주 태형산업	Certificate. No.	YR-26-09915-3
P.O. No.	ES261014-2869	Date of Issue	2026.07.09
Hull No.(Project No.)	N/A	Dimension & VI	GOOD
Spec. for Material	KS D3576 STS304 TP	Spec. for Inspection	KS B1543 STS304-W /B1500

1. ITEM DESCRIPTION

DKB LOT No	Item No	Heat No	Description	Q'TY	Starting Material	NDE(RESULT)
KDC0023	1	SD59218	TEE S/10S 40A B.W	4	WELDED PIPE	N/A
KDC0024	2	SE49720	TEE S/10S 50A B.W	3	WELDED PIPE	N/A
KDC0026	3	SD68272	TEE S/10S 80A B.W	1	WELDED PIPE	N/A

* Heat Treatment Condition : 1050℃ Solution Annealing & Water Quenching

2. CHEMICAL COMPOSITION(%)

Heat No.	Spec	C	Si	Mn	P	S	Ni	Cr
	Max	0.080	1.00	2.00	0.045	0.030	11.00	20.00
	Min	-	-	-	-	-	8.00	18.00
SD59218	L	0.066	0.37	1.03	0.033	0.004	8.09	18.22
SE49720	L	0.062	0.39	1.02	0.035	0.006	8.09	18.05
SD68272	L	0.047	0.42	1.08	0.031	0.002	8.12	18.26

* L : Ladle Analysis P : Product Analysis

3. MECHANICAL PROPERTIES

Heat No	Unit	TENSILE TEST			HARDNESS TEST	CHARPY-V IMPACT TEST (Test Temp : ℃)		
		Y.S(0.2%)	T.S	E.L		ABSORBED ENERGY (Unit:J)		LATERAL EXP.
		MPa	MPa	%	HB	Min	AVR	Min (mm)
Spec Min		205	515	35	-	-	-	-
SD59218	L,B	329	692	55	-	-	-	-
SE49720	L,B	314	661	53.8	-	-	-	-
SD68272	L,B	285	641	53.6	-	-	-	-
					-	-	-	-
					-	-	-	-
					-	-	-	-

* L : Longitudinal, T : Transvers, B : Base Metal, W : Weld Metal

Heat No	PMI	FLATTENING	CORROSION TEST	HYDROSTATIC TEST	FERRITE	GRAIN SIZE
SD59218	GOOD	N/A	N/A	N/A	N/A	N/A
SE49720	GOOD	N/A	N/A	N/A	N/A	N/A
SD68272	GOOD	N/A	N/A	N/A	N/A	N/A

REMARK:

We certify this material has been manufactured and examined in accordance with
all requirements of the specification and the results of all examination are acceptable