# Technical sheet 75488 - Electrode preparation (Li-ion)

Source: battery-device-data-qa (Hugging Face, Apache-2.0), document_id 75488. Content reworded by the team; original article paragraphs are not reproduced because their own copyright was not verified.

Electrode slurries are cast on current collectors: aluminium foil on the cathode side and copper foil on the anode side, then dried under vacuum at 90 °C overnight. The cathode to anode mass ratio is set to about 4 to balance the cell.

## Components

| Component | Value |
|---|---|
| Cathode current collector | Al foil |
| Anode current collector | Cu foil |
| Drying | 90 °C, vacuum, overnight |
| Mass ratio cathode/anode | about 4 |

Table 1: components reported

## Review note

Dataset annotates 'Al foil' as the cathode. Al foil is the current collector, not the active cathode material: annotation judged imprecise.