Technical sheet 75496 - LFP full cell electrode

Source: battery-device-data-qa (Hugging Face, Apache-2.0), document_id 75496. Content reworded by the team; original article paragraphs are not reproduced because their own copyright was not verified.

Commercial lithium iron phosphate (LFP) is the cathode material. The electrode mix is LFP, acetylene black and PVDF in a 8:1:1 mass ratio in NMP, coated on aluminium foil and dried in a vacuum oven at 80 °C.

Components

Component	Value
Cathode	LFP
Conductive additive	Acetylene black
Binder	PVDF
Ratio	8:1:1
Drying	80 °C, vacuum

Table 1: components reported

Review note

Two annotations for the same question (LFP and lithium iron phosphate (LFP)): duplicate answers.