

SEF35FP

Ceramic and fire-proof Sponge Silicone Rubber Compound

SEF35HP is an addition cured sponge silicone rubber compound with 58 shore A hardness. It is specially formulated for ceramic and fire-proof sponge applications requiring heat resistance and low compression set. It compliances with REACH and ROSH.

Key Features

- Good mechanical properties
- Excellent heat resistance
- Excellent foaming performance
- Low compression set

Applications

- Sponge parts
- Sponge sealing parts

Typical Property Data

Test Items	Unit	Test Standards	Typical Data
Density	g/ cm3	ASTM D297	1.31
Density (after foaming)	g/ cm3	ASTM D297	0.35
Color	/		Off-white
Mechanical Properties after vulcanization @125°C for 5 mins			
Shore A Hardness	/	ASTM D2240	58
Shore C Hardness (after foaming)	/	ASTM D2240	30
Tensile Strength	MPa	ASTM D412	3.0
Elongation at Break	%		180
Tear Strength	KN/m	ASTM D624 Die C	10

Compression set (after foaming) 24hrs@ 150°C , 50% compression ratio	%	ISO 815	4.8
ML(1+4) @100°C	MU	ASTM D1646	19.5

**Typical data values should not be used as specifications*

Instruction for Use

Mixing the base compound and additives in two roll mill with certain ratio of is the most suitable mixing process, The temperature during mixing must be lower than 40. After mixing put the mixed material into extruder for extrusion, suggested heating tunnel temperature is within the range from 200-300°C depends on the length of heating tunnel and product size.

The material should be stored in a cool and dry place out of direct sunlight.

Shelf Life

Three months at temperature below 25°C

Precautions for Use

This product description does not include product safety information. Note: Before using the product, read the product instructions, product safety data manual.

Package

20kg Carton

Delesun Inc

EMAIL: tech@delesungp.com

[http //:www.delesungp.com](http://www.delesungp.com)