

SEF703

Fire-resisting ceramic silicone rubber compound

SEF703 is a peroxide cured fire-resisting ceramic silicone rubber compound with 70 shore A hardness. It is specially formulated for meeting standard of BS-6387 & IEC60331 for fire resistance cable application and compliance with REACH and ROSH

Key Features

- Excellent mechanical properties
- Excellent heat resistance performance
- Excellent extrusion processability
- Easy to form ceramic layer

Applications

- Fire-resistance cables and wires
- Cable accessories

Typical Property Data

Test Items	Unit	Test Standards	Typical Data
Density	g/ cm3	ASTM D297	1.36
Color	/		Off-white
Mechanical Properties after vulcanization @125°C for 5 mins			
Shore A Hardness	/	ASTM D2240	70
Tensile Strength	MPa	ASTM D412	7.3
Elongation at Break	%		385
Tear Strength	KN/m	ASTM D624 Die C	25
Mooney-Viscosity@100°C	MU	ASTM D1646	26
Mechanical Properties after Aging in Air Oven @ 200°C for 240hrs			
Shore A Hardness	/	ASTM D2240	78
Tensile Strength	MPa	ASTM D412	5.2
Elongation at Break	%		210

IRM 901# Oil Resistance Performance after 70hrs @ 150°C			
Shore A Hardness Change	/	ASTM D2240	-2
Tensile Strength Change	%	ASTM D-412	-6
Elongation at Break Change	%		-26
Volume Change	%	ASTM D-471	+6.5
IRM 903# Oil Resistance Performance after 70hrs @ 150°C			
Shore A Hardness Change	/	ASTM D2240	-20
Tensile Strength Change	%	ASTM D-412	-32
Elongation at Break Change	%		-37
Volume Change	%	ASTM D-471	+41

Instruction for Use

Mixing the base compound and DCBP(active content 50%) in two roll mill with ratio of 100:1.2 is the most suitable mixing process, mixing time should be subject to the uniformity of the material, and the temperature during mixing must be lower than 40°C . The temperature of extruder during extrusion must be lower than 50 °C . The tunnel temperature should be within the range of from 200-300°C depends on the length of tunnel and cable size.

The material should be Stored in a cool and dry place out of direct sunlight.

Shelf Life

One year at 25°C

Precautions for Use

This product description does not include product safety information. Note: Before using the product, read the product instructions, product safety data manual, safety standards, and any physical health toxicity instructions.

Package

20kg Carton

Delesun Inc

EMAIL: tech@delesungp.com

[http //:www.delesungp.com](http://www.delesungp.com)