

Product Information



DELESUN High-Temperature Vulcanized Silicone Compound

SE2160K

DELESUN SE2160K, 60 Shore A oil-resistant silicone compound
for extrusion & compression molding, applicable to various rubber
goods

Features

- 1. Hardness: 60 Shore A
- 2. Milky white appearance
- 3. High-temperature vulcanizable (HTV)

Applications

- 1. Various automotive rubber hoses
- 2. Compression molded parts
- 3. Diverse electrical components

Advantages

- 1. Excellent process-ability
- 2. Formulated for automotive rubber hoses
- 3. Favourable flow properties

Typical Performance

Property	单位 Unit	测试方法 Test method	测试要求Test requirement	测试结果Test result
密度 Density	g/ cm3	ASTM D297	/	1.23
颜色 Color	/	/	乳白色	乳白色
Normal mechanical performance test 【175℃ *12min】 (Cold Mold Curing) Post-Curing (200℃ *4h)后				
硬度 Shore A hardness	N/A	ASTM D2240	60±5	60
扯断强度 Tensile strength	MPa	ASTM D412	≥6	7

扯断伸长断 Elongation at break	%		≥200	320
撕裂强度 Tear resistance	KN/m	ASTM D624	≥9	17.8
门尼粘度 Mooney-Viscoslty	MU	ASTM D 1646	/	24
热老化后机械性能测试 Mechanical properties after aging in air oven 【225℃ *70h】				
硬度 Shore A hardness	N/A	ASTM D2240	≤10	-1
扯断强度变化 Tensile strength	%	ASTM D412	≤-20	-15
扯断伸长率变化 Elongation at break	%		≤-30	-20
耐 901#油机械性能测试 Mechanical properties after 901# oil 【150℃ *70h】				
硬度变化 Shore A hardness	N/A	ASTM D2240	-10 to 0	-8.0
扯断强度变化率 Tensile strength	%	ASTM D-412	≤-30	-25
扯断伸长变化率 Elongation at break	%		≤-30	-29
体积变化率 Volume change	%	ASTM D-471	0 to10	7.0
耐 903#油机械性能测试 Mechanical properties after 903# oil 【150℃ *70h】				
硬度变化 Shore A hardness	N/A	ASTM D2240	≤-30	-24
体积变化率 Volume change	%	ASTM D-471	≤60	32
压缩永久变形 The compression permanent deformation 【175℃ *22h】				
变形率 rate of deformation	%	ASTM D-395	≤50	30
Aged in De-ionised-70hrs@Bpt				
硬度变化 Variation of Shore A hardness	N/A	ASTM D2240	±5	3
体积变化率 Volume change	%	ASTM D-471	±5	2
Aged in 50% De-ionised Water /50%Ethylene Glycol -70hrs@Bpt				
硬度变化 Variation of Shore A hardness	N/A	ASTM D2240	±5	3
体积变化率 Volume change	%	ASTM D-471	±5	3

Mixing Ratio: Base Compound with DBPH Curing Agent Series = 100/1.2
Curing Test Conditions: 175°C × 5min Post-Curing: 200°C × 4h

Description:



SE2160K is a 60 Shore A oil-resistant silicone compound designed for oil-resistant finished articles with balanced overall properties. It delivers excellent processability, and the base compound is readily pigmentable to achieve a wide range of custom colours. This grade is suitable for extruded parts including rubber hoses, electrical components and other related accessories. The material complies with environmental standards such as REACH and RoHS.

Instructions:

Mixing or colouring is optimally carried out on an open mill to ensure homogeneous blending of materials.

For silicone curing agent (DBPH): Recommended dosage: 1.2–1.5 phr based on base compound. Curing temperature and time depend on part dimension, thickness and molding temperature. For further information about this compound, please contact DELESUN office.

Limitations of Use:

This product is neither recommended nor tested for medical applications.

Packaging

20 kg per carton

Precautions:

This document does not contain product safety information. Prior to handling the product, please read the product specification, Material Safety Data Sheet (MSDS), safety regulations and all health & toxicity statements. You may also contact Delesun technical department or local sales representative to obtain relevant documents.

Shelf Life:

Store under ambient temperature. Validity period: 3 months from production date in original unopened packaging.

DELESUN New Materials (Shanghai) Co., Ltd.
No. 539, Kegong Road, Fengxian District, Shanghai
TEL: 021-57500370
FAX: 021-57500371