

SEM6820

耐热硅橡胶混炼胶

Heat Resistance Silicone Rubber Compound

SEM6820 是一款 67 度过氧化物及铂金硫化耐热硅橡胶混炼胶, 该产品经过特殊配方设计可以在 200 度温度下长期使用, 可以满足 EV 电缆相关标准并且符合 REACH 和 ROHS 的要求。

SEM6820 is peroxide and addition cured heat resistance silicone rubber compound with 67 shore A hardness. The product is specially formulated for high temperature resistance up to 200°C for long term and can meet the standards of for EV cable application and compliance with REACH and ROHS.

Key Features/特性

- Excellent mechanical properties/优良的物理机械性能
- Excellent heat resistance performance/优良的耐热性能
- Excellent extrusion processability/优良的挤出工艺性能

Applications/应用

- EV cable insulator /系能源汽车电缆料
- Wires requiring heat resistance/耐热电线电缆
- Heat resistance parts /耐热部件

Typical Property Data

Test Items/测试项目	Unit/单元	Test Standards/测试标准	双二四硫化	铂金硫化
Density/密度	g/ cm3	ASTM D297	1.21	1.21
Color/颜色	/		Orange	Orange
Mechanical Properties after vulcanization @120°C for 10mins 120 度 10 分钟硫化后的物理机械性能				
Shore A Hardness/硬度	/	ASTM D2240	67	67
Tensile Strength/拉伸强度	MPa	ASTM D412	10.5	9.5
Elongation at Break/断裂伸长率	%		360	450
Tear Strength/直角撕裂	KN/m	ASTM D624 Die C	22	45
Mooney-Viscosity@30°C/门尼	MU	ASTM D1646	48	50
Electrical Properties after vulcanization @120°C for 10 mins				

120 度 10 分钟硫化后的电性能				
Dielectric Strength/介电强度	kV/mm	IEC 60243	23	23
Volume Resistivity/体积电阻率	$\Omega \cdot \text{mm}$	IEC 60093	1.4×10^{16}	1.8×10^{16}

Mechanical Properties after Aging in Air Oven @ 205°C for 10days 205 度 10 天老化后物理机械性能				
Shore A Hardness/硬度	/	ASTM D2240	72	72
Tensile Strength/拉伸强度	MPa	ASTM D412	8.2	6.8
Elongation at Break/断裂伸长率	%		220	280
Mechanical Properties after Aging in Air Oven @ 250°C for 10days 250 度 10 天老化后的物理机械性能				
Shore A Hardness/硬度	/	ASTM D2240	75	74
Tensile Strength/拉伸强度	MPa	ASTM D412	7.3	5.4
Elongation at Break/断裂伸长率	%		150	153
Mechanical Properties after Aging in Air Oven @ 200°C for 3000hrs 200 度 3000 小时老化后的物理机械性能				
Shore A Hardness/硬度	/	ASTM D2240	78	77
Tensile Strength/拉伸强度	MPa	ASTM D412	6.4	5.0
Elongation at Break/断裂伸长率	%		101	117

Instruction for Use/使用说明

用双辊开炼机将基胶和各种添加剂按照比例混合，混合过程物料的温度不得超过 40 度。将混合好的物料投入挤出机进行挤出，建议挤出过程烘道的温度为 500-800 度之间，具体温度设置取决于产品尺寸，烘道的长度和挤出速度。

材料应该存储在阴凉干燥的地方，避免阳光直晒。

Mixing additives and color pastes in two roll mill is the most suitable mixing process, mixing time should be subject to the uniformity of the material, and the temperature during mixing must be lower than 40°C. Suggested heating tunnel temperature is within the range of from 500-800°C, depends on the cable size, length of tunnel and extrusion speed.

The material should be Stored in a cool and dry place out of direct sunlight.

Shelf Life/有效期

不超过 25 度条件下有效期为 1 年

One year at temperature below 25°C

Precautions for Use/注意事项

产品瞄准不包括产品安全数据信息。建议使用前阅读产品说明，安全数据表。

This product description does not include product safety information. Note: Before using the

product, read the product instructions, product safety data manual, safety standards, and any physical health toxicity instructions.

Package/包装

20 公斤纸箱

20kg Carton

Delesun Inc

EMAIL: tech@delesungp.com

[http //:www.delesungp.com](http://www.delesungp.com)