

Product Information

DELESUN High-Temperature Vulcanized Silicone Rubber



SEN671

DELESUN EN107 is a 70 Shore A silicone compound for extruded wire & cable applications. It complies with the 107 standard specified in EN50382, and is widely used for railway and high-speed train cable products.

Features:

1. 70 Shore A hardness
2. Black
3. Designed for extrusion processing

Advantages:

1. Flame retardant and medium resistance
2. Outstanding ageing performance
3. High light transmittance

Applications:

1. Various electric wires
2. Power cables
3. General electrical parts

Typical Performance

Property	单位 Unit	测试方法 Test method	测试要求 Test requirement	测试结果 Test result
密度 Density	g/ cm3	ASTM D297	/	1.25
颜色 Color	/		黑色	黑 色
硬度 Shore A hardness	N/A	ASTM D2240	70±5	70

扯断强度 Tensile strength	MPa	ASTM D412	≥8	10.5
扯断伸长断 Elongation at break	%		≥200	420
撕裂强度 Tear resistance	KN/m	ASTM D624	≥20	25
门尼粘度 Mooney-Viscoslty	MU	ASTM D1646	/	19.5
热老化后机械性能测试 Mechanical properties after aging in air oven 【200℃*240h】				
硬度 Shore A hardness	N/A	ASTM D2240	/	76
扯断强度 Tensile strength	MPA	ASTM D412	≥6	6.9
扯断伸长率 Elongation at break	%		≥160	253
耐 901#油机械性能测试 Mechanical properties after 902# oil 【100℃*24h】				
硬度变化 Shore A hardness	N/A	ASTM D2240	/	-4
扯断强度变化率 Tensile strength	%	ASTM D-412	≤±25	-11
扯断伸长变化率 Elongation at break	%		≤±30	-7
体积变化率 Volume change	%	ASTM D-471	/	8.5
耐酸性能测试 Mechanical properties after acid 【23℃*168h】				
扯断强度变化率 Tensile strength	N/A	ASTM D2240	≤±30	-25
扯断伸长变化率 Elongation at break	%	ASTM D-412	≥100	419
耐碱性能测试 Mechanical properties after alkali 【23℃*168h】				
扯断强度变化率 Tensile strength	N/A	ASTM D2240	≤±30	-4
扯断伸长变化率 Elongation at break	%	ASTM D-412	≥100	523

Mixing Ratio: Base Compound / Curing Agent

(DBPH Series) =100/1.2

Curing Test Conditions: 175℃×5min Post-Curing

Conditions: 200℃×4h

Description:

EN107 is a 70 Shore A extrusion silicone compound for wire and cable applications with well-balanced overall properties. It offers excellent processability. The standard colour is black, and custom colours are available upon request. Suitable for extruded components including wires, cables and other related accessories. This material complies with environmental standards including REACH and RoHS.

Instructions

Mixing and colouring are best performed on an open mill to ensure homogeneous mixing. Recommended addition of Delesun silicone curing agent (DBPH): 1.0 –1.2 phr base compound. Curing temperature and time vary with cable size, thickness and curing tunnel length. Contact Delesun office for more technical details.

Precautions:

This datasheet excludes safety information. Prior to use, please review product specification, SDS, safety regulations and health hazard information. You can contact Delesun technical team or local sales representative to obtain relevant documents.

Shelf Life

Stored at ambient temperature in original packaging; minimum validity period: 6 months from production date.

Limitations of Use:

This product is neither recommended nor tested for medical applications.

Packaging:

20 kg per carton

DELESUN New Materials (Shanghai) Co., Ltd.
No. 539, Kegong Road, Fengxian District, Shanghai
TEL: 021-57500370
FAX: 021-57500371