

SE2270G

High Strength Silicone rubber compound

SE2270G is a peroxide cured silicone rubber compound with 70 shore A hardness. It is specially formulated for the applications requiring high mechanical properties and compliance with REACH and ROSH.

Key Features

- Excellent mechanical properties
- Excellent tear strength
- Excellent extrusion processability
- Easy to match different colors

Applications

- Extruded parts & cable

Typical Property Data

Test Items	Unit	Test Standards	Typical Data
Density	g/ cm3	ASTM D297	1.19
Color	/		Translucent
Mechanical Properties after vulcanization @125°C for 10 mins			
Shore A Hardness	/	ASTM D2240	70
Tensile Strength	MPa	ASTM D412	11
Elongation at Break	%		480
Tear Strength	KN/m	ASTM D624 Die B	27
Mooney-Viscosity@30°C	MU	ASTM D1646	53

**Typical data values should not be used as specifications*

Instruction for Use

Mixing the base compound and DCBP(active content 50%) in two roll mill with ratio of 100:1.5 is the most suitable mixing process, mixing time should be subject to the uniformity of the material,

and the temperature during mixing must be lower than 40°C.

The material should be stored in a cool and dry place out of direct sunlight.

Shelf Life

One year at the temperature below 25°C

Precautions for Use

This product description does not include product safety information. Note: Before using the product, read the product instructions, product safety data manual, safety standards, and any physical health toxicity instructions.

Package

20kg Carton

Delesun Inc

EMAIL: tech@delesungp.com

<http://www.delesungp.com>