


# Comparison of CEM I 42.5R vs CEM I 52.5N



Cumulated Heat at 24 h (cutoff  $\geq 15$  min)

Bindemittel	index	cumulated_heat_at_hours	target_h	cutoff_min
nan	0	134.19	24	15
nan	1	166.52	24	15