

ABLUSOFT NAK-P

ABLUSOFT NAK-P is an excellent nonionic softener. It imparts a smooth, soft hand and antistatic properties on cottons, synthetics and its blends. As its excellent nonyellowing property, it can be used in fluorescent whitening fibers. It also can be used to advantage in resin finishing.

General Properties:

White pastille Appearance

Composition Fatty acid derivative

Ionic **Nonionic** pH (1% aq.) 9 + 1

Solubility Can disperse completely in hot water (above 60° C)

2. Features:

- Very soft handle on cottons, synthetics and its blends.
- Non-yellowing property, can use in fluorescent whitening fibers.
- Can combine with most of the usual products used in finishing.

Application: 3.

- 1). **ABLUSOFT NAK-P** is dissolved by 1 part to 9 part water, giving a 10% solution.
- 2). **ABLUSOFT NAK-P** should be added to the required quantity of water at 60° C or above 60°C and stirring up for approximately 1 hour until completely dissolved. Stirring must be continued during cooling in order to avoid the formation of a surface skin which may contaminate the final product.
- 3). **ABLUSOFT NAK-P** is usually applied on padding process.
- 4). The amount of ABLUSOFT NAK-P depends on the kind of fibers, the form of goods and the handle required. In general, ABLUSOFT NAK-P (10%) is applied at 10 - 50 g/L.





總公司:台北市中山北路一段11號8樓 電話:(02)2541-0022 傳直:(02)2542-3773 觀音廠: 桃園觀音工業區成功路一段514號 電話: (03)483-9421 傳真: (03)483-9140

Head Office: 8Fl., No.11, Sec.1, Chung Shan North Road, Taipei, Taiwan Phone: (02)2541-0022 Fax: (02)2542-3773

E-Mail: twsa@ms2.hinet.net http://www.taiwansurfactant.com.tw 1st Factory: No.514, Cheng-Kung Road, Sec.1, Kwang-Inn Industrial Area, Taoyuan Country, Taiwan Phone: (03)483-9421~3 Fax: (03)483-9140



4. Operation Instruction:

Agent: ABLUSOFT NAK-P (10%)

Exhaustion:

Dosage: 3% o.w.f.

T.t.: $40^{\circ}50^{\circ}C \times 20' \rightarrow Dry \rightarrow Set. 160^{\circ}C \times 1'$

5. Packing: ABLUSOFT NAK-P is supplied in 25 kg bag.





ISO 9001:2000

022

Hitp://www.taiwansuriactant.com.tw 1st Factory: No.514, Chene, Kung Road, Sec. I, Kwang-Inn Industrial Area, Taoyuan Country, Taiwan Phone: (03)483-9421~3 Fax: (03)483-9140