

ABLUSOFT OA-400

Liquid Softener

ABLUSOFT OA-400 is an Imidazoline type ammonium cationic soft agent, it has good anti-static performance and it imparts swelling feeling.

ABLUSOFT OA-400 is also the main component for household soft agent.

General Properties

Appearance (at 25 °C): Yellowish viscous liquid

Ionicity: Cationic

pH (5%, H2O:IPA=1:1): 4.5 - 7.5

Product Features

- Is a high concentration product, and can be dissolved in warm water easily.
- · Imparts swelling and lubricant feel.
- Is the main component for household softening agent.
- Imparts excellent anti-static property for fabrics.

Application

ABLUSOFT OA-400 can be applied to the textiles by dipping or padding.

Dissolving method

For 10% solid content dilution, put 10 kg of ABLUSOFT OA-400 into mixer then mixed with 90 kg of warm water.

Guide recipes

ABLUSOFT OA-400 is diluted to 10 - 15%.

General dosage:

A. Padding: 10 - 40 g/L

B. Exhaustion: 1.0 - 4.0% o.w.f.

Shanghai Factory: No.111, Chun Hua Rd., Jinshan Industry Zone, No.2, Jinshan Dist., Shanghai, China



Storage

All products should be stored in a cool, dry, well-ventilated and without direct sunlight location, as well as stored in the original packages (eg. originally packed drum). Providing all those conditions met, the product purchased should be able to retain its full efficacies for one year, from the date of manufacture.

Packaging

120 kg / drum

Safety and Handling

Please refer to our Safety Data Sheet.

Taiwan Surfactant Corp. ABLUSOFT OA-400 - TDS - en - 09/08/2020

The indications given herein correspond to practical experiences. Owing to the difference in local conditions they cannot claim to be completed, so that any liabilities - also with a view to claims of third parties - are excluded.

總公司: 104台北市中山北路一段11號8樓電話: (02)2541-0022傳真: (02)2542-3773Head Office: 8FI., No.11, Sec.1, Chung Shan N. Rd., Taipei 104, Taiwan観音廠: 328桃園市觀音工業區成功路一段514號電話: (03)483-9421傳真: (03)483-9140Phone: +886-2-2541-0022Fax: +886-2-2542-3773

上海廠:上海市金山區金山第二工業區春華路111號 電話:86-21-6726-2323 傳真:86-21-6726-1137 E-Mail:twsa@twsa.com.tw Website: www.taiwansurfactant.com

Phone: +886-3-483-9421 Fax: +886-3-483-9140

Shanghai Factory: No.111, Chun Hua Rd., Jinshan Industry Zone, No.2, Jinshan Dist., Shanghai, China