

# TEGOPREN® 6923

## Product description

TEGOPREN® 6923 is a self-dispersible quaternary silicone for hydrophilic textile finishing.

## Physical properties

Appearance (25 °C)	yellow liquid
Viscosity (Brookfield, 25 °C)	3 500 – 7 500 mPas
Active content (%)	min. 95 %
Propylene glycol content	max. 5 %
Weight % quat. Nitrogen	0.4 – 0.5

## Application fields

TEGOPREN® 6923 is recommended as substantive, high performance softening agent with rewetting properties ideal for textile applications.

TEGOPREN® 6923 provides excellent softness for non-wovens and fabrics made of native or synthetic fibers. It is also recommended as a component for diverse preparations.

## Benefits

TEGOPREN® 6923 gives outstanding softening performance, hydrophilicity and excellent non-yellowing behavior.

TEGOPREN® 6923 is self-dispersible in cold water when used up to 10% actives. For higher concentrations only minimal amounts of emulsifier are required to stabilise the micro-emulsion.

TEGOPREN® 6923 micro emulsions show good stability at high shear rates.

## Dosage/Handling

TEGOPREN® 6923 can be applied by the exhaust method or by padding.

For padding applications we recommend a dosage of approx. 2 – 8 g/l TEGOPREN® 6923.

For the exhaust method we recommend approx. 0.1 – 0.8 % TEGOPREN® 6923 (based on textile weight) at a temperature of 40°C for a duration of approx. 20 min.

## Registration status

The components of TEGOPREN® 6923 are listed in the following inventories:

EINECS, TSCA, ENCS, AICS, ECL, PICCS and China

## Storage stability

12 months in original sealed containers at room temperature.

## Packaging

50 kg plastic drums  
Pallet size: 6 x 50 kg = 300 kg  
200 kg plastic drums  
Pallet size: 4 x 200 kg = 800 kg

## Hazardous goods classification

Information concerning

- classification and labelling according to regulations for transport and for dangerous substances
- protective measures for storage and handling
- measures in case of accidents and fire
- toxicity and ecological effects

is given in our material safety data sheets.

## Guide Formulations

### 10 % Formulation

Product	%
TEGOPREN® 6923	10.0
Water	90.0

### Processing

Add water into vessel, start to stir.

Add TEGOPREN® 6923 into the water and keep stirring for about 30 minutes to clear emulsion.

Adjust pH value to 5.5 – 6.5.

## Guide Formulations

### 20 % Formulation

Product	%
TEGOPREN® 6923	21.0
Lauryl fatty alcohol · 6 EO	5.0
Butyl di glycol	2.0
Acetic Acid, 99%	0.5
Water	61.5

### Processing

Add water, acetic acid, FAEO and BDG into vessel while stirring until homogenous. Stir for about 10 minutes.

Then add TEGOPREN® 6923 into the above mixture. Start to stir and keep stirring for about 50 minutes until a clear emulsion is observed.

Adjust pH value to 5.5 – 6.5.

07/2015

### Trademark notice and legal notice

This information and all further technical advice are based on our present knowledge and experience. However, it implies no liability or other legal responsibility on our part, including with regard to existing third party intellectual property rights, especially patent rights. In particular, no warranty, whether express or implied, or guarantee of product properties in the legal sense is intended or implied. We reserve the right to make any changes according to technological progress or further developments. The customer is not released from the obligation to conduct careful inspection and testing of incoming goods. Performance of the product described herein should be verified by testing, which should be carried out only by qualified experts in the sole responsibility of a customer. Reference to trade names used by other companies is neither a recommendation, nor does it imply that similar products could not be used.

(Status: July 2015)

### Evonik Nutrition & Care GmbH

Goldschmidtstr. 100, 45127 Essen, Germany

Phone Europe +49 201 173-2665, Asia +86 21 61191 125, Americas +1 804 727 0700

interface-performance@evonik.com, [www.evonik.com/interface-performance](http://www.evonik.com/interface-performance)