

General Description

A super premium quality, 100% acrylic exterior soft gloss finish. Aura® Exterior combines the advantages of our proprietary Colour Lock® Technology, Gennex® Colour Technology, and latest resin technology to provide the ultimate exterior coating. Suitable for a variety of exterior substrates to provide a durable long-lasting finish with rich colours that resist fading and stand up to rain, snow, wind, and UV damage.

- Excellent fade resistance and gloss retention
- Proprietary Colour Lock® Technology for unparalleled colour depth
- Breathable coating less prone to blistering, providing long-term durability
- Low temperature application down to 1.7 °C
- Limited Lifetime Warranty
- Engineered with Gennex® Colour Technology
- Dirt pick-up resistant

Usage

Exterior surfaces such as wood, fiber cement board, hard board, vinyl and aluminum siding, shakes, unglazed brick, concrete, stucco, cinder block and primed metal.

Colours	White (01)
Bases	1X, 2X, 3X, 4X
Colorant System	Gennex®

Technical Data

Vehicle	Proprietary 100% Acrylic		
Pigment	Titanium Dioxide		
Volume Solids	40 ± 2%		
Spread Rate Per 3.79 L	32.5 – 41.8 sq. m. (350 – 450 sq. ft.)		
Recommended	Wet:	3.6 – 4.6 mils	
Film Thickness	Dry:	1.4 – 1.8 mils	
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.			
Dry Time @ 25 °C (77 °F) @ 50% RH	To Touch:	1 hour	
	To Recoat:	4 hours	
Painted surfaces can be washed after two weeks. High humidity and cool temperatures will result in longer dry, recoat and service times.			
Surface Temperature	Min:	1.7 °C (35 °F)	
During Application	Max:	37.7 °C (100 °F)	
Viscosity	100 ± 4 KU		
Flash Point	None		
Sheen / Gloss	50 – 60 @ 60°		
Clean Up	Water		
Thinner	refer to page 2		
Weight Per 3.79 L	4.9 kg (10.8 lbs.)		
Storage Temperature	Min:	4.4 °C (40 °F)	
	Max:	32.2 °C (90 °F)	
VOC	< 50 g/L		

Primer Systems

Aura® Waterborne Exterior is self-priming on most properly prepared substrates, including wood, fiber cement board, hardboard, nonferrous metals and cured masonry surfaces. **Special Note:** Certain custom colours require a Deep Colour Base Primer tinted to a special prescription formula to achieve the desired colour. Consult your retailer.

Wood, and engineered wood products:

Self-priming

Bleeding Woods (Redwood, Cedar, etc.):

Fresh Start® Exterior Deck & Siding Primer (K094) or Fresh Start® High-Hiding All Purpose Primer (K046)

Hardboard Siding, Bare or Factory Primed:

Self-priming

Vinyl Siding & Vinyl Composite:

In most cases, a primer is not necessary. Only areas of pitted and porous vinyl siding must be primed. In these cases, we recommend Fresh Start® High-Hiding All Purpose Primer (K046)

Colours that are safe for use on vinyl siding - Do not paint vinyl with any colour darker than the original colour or having a Light Reflective Value (LRV) of less than 57 unless it is in the Benjamin Moore approved Colours for Vinyl palette and complies with the specific vinyl manufacturer guidelines when making the colour selection and painting. Otherwise, the colour will absorb more heat, possibly causing the siding to warp, resulting in additional repairs and expenses.

Rough or Pitted Masonry:

Ultra Spec® Masonry Interior/Exterior Hi-Build Block Filler (K571)

Poured or Pre-cast Concrete/Fiber Cement Siding:

Self-priming. New masonry substrates must be allowed to fully cure for 30 days before painting.

Ferrous Metal (Steel and Iron):

High Performance Acrylic Metal Primer (HP1100) or High Performance Alkyd Metal Primer (HP1320)

Non-Ferrous Metal (Galvanized & Aluminum):

All new metal surfaces must be thoroughly cleaned with Oil & Grease Emulsifier (HP6000) to remove contaminants. New shiny non-ferrous metal surfaces that will be subject to abrasion should be dulled with very fine sandpaper or a synthetic steel wool pad to promote adhesion.

Self-Priming. For additional rust protection, prime with Acrylic Metal Primer HP1100.

Limitations

- Do not apply when air or surface temperatures are below 1.7 °C (35 °F).
- For Wind-Driven Rain over smooth and stable masonry only (non-elastomeric use). Follow primer instructions.
- Not recommended for walking surfaces.

Compliance & Certifications

ASTM D6904	Pass: (< 0.2)
Wind Driven Rain	
1 coat Masonry Sealer - 1-2 coats F632	
ASTM D1308	Pass
Alkali Resistance	
1 coat Masonry Sealer - 1-2 coats F632	
ASTM D1653	25.3 perms
Water Vapor Permeance	
ASTM D3273/D3274	Pass: No Growth
Mildew Resistance Test	
ASTM D522/522M	Pass: No Cracking
Flexibility	
ASTM D2370 Elongation & Tensile Strength	108 % 874 PSI
MPI	311

LIFETIME LIMITED WARRANTY: Benjamin Moore & Co., Limited warrants that this product, when used in accordance with the label instructions, will not: 1. blister from properly prepared and primed surfaces; 2. peel from properly prepared and primed surfaces; and 3. wear down or weather to expose the previously painted surface. This limited warranty shall be effective for so long as you reside in your home and is made to the original residential consumer paint purchaser. This limited warranty is non-transferable. If this product fails to perform as explained above when used according to label instructions within the warranty period, Benjamin Moore & Co., Limited will, upon presentation of proof of purchase (original sales receipt), provide an equivalent or comparable product at no charge. Since we have no control over surface preparation or application, this limited warranty does not include the cost of labour for application of paint. Benjamin Moore & Co., Limited shall in no event be liable for indirect, special, incidental or consequential damages, including economic loss. This limited warranty gives you specific legal rights and is applicable to products sold in Canada. You may also have other rights, which vary from province to province. EXCEPT AS SET OUT ABOVE OR PURSUANT TO APPLICABLE LAWS, THE LIMITED WARRANTY PROVIDED ABOVE IS THE SOLE AND EXCLUSIVE WARRANTY PROVIDED BY BENJAMIN MOORE & CO., LIMITED TO YOU FOR THIS PRODUCT AND IS IN LIEU OF ALL OTHER WARRANTIES, EXPRESS OR IMPLIED, WHETHER ARISING OUT OF OPERATION OF LAW OR OTHERWISE.

Technical Assistance

Available through your local authorized independent Benjamin Moore retailer.

call 1-800-361-5898
visit www.benjaminmoore.ca

Surface Preparation

Surfaces must be clean, dry and free of oil, grease, wax, rust, mildew, chalk and loose or scaling paint. Cement based water proofing paints should be removed. Glossy surfaces must be dulled. Un-weathered areas such as eaves, porch ceilings, overhangs and protected wall areas should be washed with an appropriate cleaner and rinsed with a strong stream of water from a garden hose or power washer to remove contaminants that can interfere with proper adhesion.

All new masonry surfaces must be power washed or brushed thoroughly with stiff fiber bristles to remove loose particles. New masonry substrates must be allowed to cure for 30 days before priming or painting. Poured or pre-cast concrete with a very smooth surface should be etched or abraded to promote adhesion, after removing all form release agents and curing compounds.

Difficult Substrates: Benjamin Moore offers a number of specialty primers for use over difficult substrates such as bleeding woods, grease stains, crayon markings, hard glossy surfaces, or other substrates where paint adhesion or stain suppression is a particular problem. Your Benjamin Moore retailer can recommend the right problem-solving primer for your special needs.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

Application

Stir thoroughly before and during use. Apply one or two coats. For best results, use a premium Benjamin Moore® custom-blended nylon/polyester brush, premium Benjamin Moore® roller, or a similar product. Apply paint generously from unpainted area into wet area.

Brush: Nylon / polyester

Roller: Premium Quality

Spray, Airless:

Pressure / 1,600 – 2,600 PSI

Tip / 0.013 – 0.015

Under normal application conditions Aura® may be sprayed to achieve a high build one coat system over properly prepared substrates that are in good condition. Refer to Surface Preparation / Priming Sections for appropriate priming and preparation information.

Thinning/Cleaning

Conditioning with Benjamin Moore® K518 Extender may be necessary under certain conditions to adjust open time or spray characteristics.

Add K518 Extender or water - Max of 236 mL to 3.79 L of paint

Never add other paints or solvents.

Clean Up: Wash brushes, rollers, and other painting tools in warm soapy water immediately after use. Spray equipment should be given a final rinse with mineral spirits to prevent rusting.

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**