



Epoxy Pool Coating

Semi-Gloss Finish IG-40XX

General Description

Epoxy Pool Coating is a two-component, polyamide epoxy designed for properly prepared concrete, plaster, fibreglass, steel, and previously coated epoxy pool surfaces. It is extremely durable in fresh and salt water and resists common pool chemicals, including chlorine. **This is a two-component product with a mix ratio of 1:1. It requires 1 part of component "A" or Base mixed with 1 part of component "B" or Catalyst. Do Not Mix Partial Kits.**

- Use with fresh or salt water
- Two-component coating
- Resistant to common pool chemicals

Usage

Epoxy Pool Coating is designed for use on concrete, marcite, gunite, fibreglass and steel surfaces. The integrity of the marcite or gunite must be sound and solid. Epoxy Pool Coating, like any epoxy coating, will chalk and fade over time when exposed to ultraviolet light. Not for use in hot tubs or spas.

Colours	White (10), Black (20), Ocean Blue (42), Royal Blue (24)
Bases	N/A
Colorant System	Industrial Colorants (Up to 60 mL may be added per 3.79 L of Part A)

Technical Data

Vehicle	Polyamide Epoxy
Pigment	Titanium Dioxide
Volume Solids	62 ± 2%
Spread Rate Per 3.79 L	32.5 – 37.2 sq. m. (350 – 400 sq. ft.)
Recommended	Wet: 4.0 – 4.6 mils
Film Thickness	Dry: 2.5 – 2.8 mils
Depending on surface texture and porosity. Be sure to estimate the right amount of paint for the job. This will ensure colour uniformity and minimize the disposal of excess paint.	
Dry Time @ 25 °C (77 °F) @ 50% RH	To Touch: 2 hours To Recoat: 3 – 72 hours Full Cure: 7 days outdoor 14 days indoor
*If top coat is not applied within 72 hours abrade the surface to ensure proper inter-coat adhesion. Maximum abrasion and chemical resistance are achieved at full cure; care should be taken to prevent damage to the coating during the curing process. High humidity and cool temperatures will result in longer dry, recoat and cure times.	
Surface Temperature During Application	Min: 10 °C (50 °F) Max: 37.8 °C (100 °F)
Viscosity	90 ± 4 KU > 26.7 °C (80 °F)
Flash Point	(TT-P-141, Method 4293)
Sheen / Gloss	40 – 50 @ 60°
Clean Up	Xylene or HP7040
Thinner	Do not thin
Mixed Ratio (by volume)	1 : 1
Induction time @ 25 °C (77 °F)	30 minutes
Pot Life @ 25 °C (77 °F)	6 hours
Weight Per 3.79 L	5.2 kg (11.5 lbs.)
Storage Temperature	Min: 10 °C (50 °F) Max: 32.2 °C (90 °F)
VOC	< 340 g/L

Surface Preparation

The following is a basic guide only. Refer to the INSL-X® "Epoxy Pool Painting Guide" for complete instructions regarding preparation and application. Surfaces to be painted must be clean, dry and free from all oils and grease. Use a heavy-duty citrus based cleaner or degreaser. Hand scrub at the water line where oils from suntan lotion will tend to migrate.

Unpainted Concrete / Plaster (Marcite, Gunite, Diamond Brite®):

These substrates must be allowed to completely cure until the surface pH is 9 or less. Verify the pH in multiple areas or allow a minimum curing period of 30–60 days prior to coating. Once fully cured and thoroughly cleaned, new or previously unpainted surfaces must be etched using INSL-X® Concrete Etch or a 10% muriatic acid solution. Apply evenly until surface reaction (bubbling/fizzing) ceases. It is extremely important that all acid residue is completely neutralized and rinsed away. Neutralize using a solution of 1 lb. baking soda per 5 gallons of water. After neutralizing, triple-rinse thoroughly with clean water and allow the surface to dry for a minimum of 3 days prior to coating.

Note and precaution: Always pour acid into the water to dilute. NEVER POUR WATER INTO THE ACID TO DILUTE.

Unpainted Fibreglass:

Following a thorough cleaning, new or previously unpainted fiberglass should be scuff sanded with 150 – 180 grit sandpaper or equivalent. Rinse off sanding dust and allow to dry 24 hours.

Unpainted Steel:

Following a thorough cleaning, inspect for rust. Remove rust following Hand Tool Cleaning (SSPC-SP2) or Power Tool cleaning (SSPC-SP3).

Previously Painted Pools:

If a previous paint exists and is in good condition, determine the type of pool paint previously used. **Epoxy Pool Coating can only be applied over another paint if the previous paint was also a 2-part epoxy.** Scrub surface with a heavy duty citrus based cleaner / degreaser to get rid of all chalk, scum, oil, dirt and suntan lotions. Flush with plenty of clean water and let dry. Scuff sand with 100 – 150 grit sandpaper or equivalent. Rinse off sanding dust and allow to dry 24 hours.

Do not acid etch a previously coated surface.

Compliance & Certifications

VOC compliant in all regulated areas.

Priming

Steel: Prime with High Performance Epoxy Mastic HP4600.

Concrete, Marcite, Gunite: Self-priming. Follow surface preparation listed above.

Previously Painted Surfaces: Self-priming. **Epoxy Pool Coating can only be applied over another paint if the previous paint was also a 2-part epoxy.** Follow surface preparation instructions.

NOTE: Painting over many old layers of pool paint is not recommended and could result in premature adhesion loss. Once multiple layers (4 or more) of paint have been applied and have aged, consideration should be given to removing all old layers back down to the substrate prior to the next paint application. When in doubt, check the adhesion of previous paint layers before proceeding.

Limitations

- Do not apply this coating over chlorinated rubber, rubber-based or water-based pool paints.
- Do not paint in direct sunlight.
- Do not paint if rain is expected in 4 – 6 hours.
- Do not use in hot tubs and spas due to high water temperatures.
- Not recommended for aluminum, stainless steel, galvanized, or vinyl-lined pools.

Technical Assistance

Available through your local authorized independent retailer.

call 1-866-708-9180
visit www.insl-x.ca

Mixing Instructions

This is a two-component product and is pre-proportioned for error free mixing. Mix "A" & "B" separately.

1.) Carefully empty the entire contents of IG-04XX Part B and the contents of IG-04XX Part A component resin into a separate metal pail, large enough to hold both Part A and Part B, scraping the sides of both parts to ensure all liquid has been added.

2.) Using a drill mixer at low speed, blend this mixture for three to five minutes until completely blended. Keep the mixing blade turning at a slow speed to minimize whipping air into material. Scrape sides of pail during the mixing process.

3.) Allow to induct for 30 minutes at 25 °C (77 °F) prior to application.

Pot Life:

6 hours at 25 °C (77 °F)

3 hours at 32.2 °C (90 °F)

Application

This product is formulated to be applied without thinning. The product may be applied by brush, roller, or spray; roller application is preferred. Follow the recommended spread rates and do not apply heavier than specified. Always apply two coats of pool paint. Use a short-nap roller only—longer nap rollers can apply excessive paint, which may lead to blistering. Two thin coats are recommended rather than one heavy coat, as over-application can cause premature pool paint failure.

Brush: Synthetic bristle.

Roller: Nylon or other synthetic roller cover. 10 mm – 13 mm (3/8" – 1/2") nap.

Spray, Airless:

Pressure / 2,000 – 2,500 PSI

Tip / 0.015 – 0.021

Filter / 60 mesh

NOTE: If more than 72 hours (25 °C/77 °F) elapses between coats, sand the film with 150-180 grit to provide sufficient profile. Do not apply this product if the material, substrate or ambient temperature is below 10 °C (50 °F) or above 37.8 °C (100 °F). Do not paint if surface temperature is within 5 degrees of the dew point. Wherever possible, avoid painting in direct sunlight.

IMPORTANT SAFETY NOTE: All glossy surfaces can be slippery. Where non-skid properties are required, a non-skid additive should be used.

Do not fill the pool before the paint has fully cured. Allow a minimum of 7 to 14 days after the final coat before filling with water—7 days for outdoor pools and 14 days for indoor pools. For both, provide forced ventilation using fans or blowers to circulate air and prevent solvent vapor buildup, which can slow final cure. Direct airflow both across the pool surface and down into the pool, paying particular attention to low-lying areas and the deep end of indoor pools where vapors tend to collect. If rainwater enters the pool before full cure is achieved, pump it out as soon as possible.

Never cover the pool with a tarp or solar blanket during cure. This could trap solvent in the coating.

All pool paints will eventually fade in colour when exposed to chlorine. Maximum colour fastness can be achieved by maintaining proper chemical balances. Do not over-chlorinate. After refilling pool, add concentrated chlorine or chlorine shock through a chlorinator or into the skimmer trap to avoid having concentrated chlorine come in contact with the new paint.

For exterior pools, allow 7 days after the final coat is applied before filling. Allow 14 days before filling indoor pools.

Clean Up

Wash brushes, rollers, and other painting tools with Xylene or HP7040 Epoxy Thinner immediately after use followed by warm soapy water. Do not allow material to remain in hoses, gun or spray equipment.

USE COMPLETELY OR DISPOSE OF PROPERLY. Dry, empty containers may be recycled in a can recycling program. Local disposal requirements vary; consult your sanitation department or state-designated environmental agency on disposal options.

Environmental Health & Safety Information

Use only with adequate ventilation. Do not breathe spray mist or sanding dust. Ensure fresh air entry during application and drying. Avoid contact with eyes and prolonged or repeated contact with skin. Avoid exposure to dust and spray mist by wearing a NIOSH approved respirator during application, sanding and clean up. Follow respirator manufacturer's directions for respirator use. Close container after each use. Wash thoroughly after handling.

WARNING! If you scrape, sand, or remove old paint, you may release lead dust. LEAD IS TOXIC. EXPOSURE TO LEAD DUST CAN CAUSE SERIOUS ILLNESS, SUCH AS BRAIN DAMAGE, ESPECIALLY IN CHILDREN. PREGNANT WOMEN SHOULD ALSO AVOID EXPOSURE. Wear a NIOSH approved respirator to control lead exposure. Clean up carefully with a HEPA vacuum and a wet mop. Before you start, find out how to protect yourself and your family by logging onto Health Canada @ <https://www.canada.ca/en/health-canada/services/environmental-workplace-health/environmental-contaminants/lead/lead-information-package-some-commonly-asked-questions-about-lead-human-health.html>

**KEEP OUT OF REACH OF CHILDREN
PROTECT FROM FREEZING**

**Refer to Safety Data Sheet for additional
health and safety information.**