



Renner USA Corp.
651, Michael Wylie Drive
Charlotte, NC 28217

YOxx.1061-Colors

WB Topcoat for Exterior - xx Sheen

Main properties:

• Exceptional weathering resistance and UV protection	• User friendly application
• Superior hardness	• High coverage
• Indoor and outdoor application	• HAPs Free

Versions:

YO10.1061.609AUS	Larice / 10 gloss	YO40.1061.609AUS	Larice / 40 gloss	YO30.1061.02US	White / 30 gloss
YO30.1061.609AUS	Larice / 30 gloss	YO60.1061.609AUS	Larice / 60 gloss		

Recommended use:	• Furniture	• Doors	• Windows
Application method:	Spray		
Blending instructions	Can be crosslinked at 1% YC.1402US or 5% YC.1018US to improve chemical and physical resistance. Add the crosslinker in weight, mixing very well with a spatula. Wait 10-15 minutes before application. Can be diluted with water maximum 10%, more than this can interfere in the film's resistance.		

Chemical-physical properties (25 °C/77°F)

Solids content (%)	Weight: 42 to 47%
Specific gravity (g/cm ³)	1.028 to 1.176
Viscosity 25°C/77°F	90 ± 5 Krebs Stormer

Application properties

Pot Life	4h
Recommended N° of coats	2-3
Recommended quantity per coat (g/m ²)	100

General remarks on the application system

Drying at 20°C/68°F and 45 – 65 RU% : 100 g/m ²	
Sanding	2 hr
Handling	2 hr
Recoating	2 hr
Stackable	36 hr (crosslinked)

Forced drying: 100 g/m ²		
	Temperature	Time
Flash Off	25°C/77°F	2 min
Laminar air	60°C/140°F	8 min
Jet air	60°C/140°F	-
Cooling	20°C/68°F	10 min
Stackable	24 hr (crosslinked)	
Sanding	Right after dried	
Re-coating	Right after sanded	

Substrate preparation Ensure the surface is clean and dry. Substrate must be free of grease, oil, dirt, fingerprints, and any other contamination to ensure optimum adhesion and coating performance properties. Sand the wood with 180-240 grit.

Application instructions: Spray 2 coats of YI.1254.00US before the White topcoat YOxx.1061.02US, and YI.1254-Color before spraying the Larice topcoat YOxx.1061.609AUS. Follow instructions of YI.1254-Colors' TDS. Dry according to indication, and sand 320 or 360 grit. Spray 2 to 3 coats of YOxx.1061-Colors (4 wet mils), drying and sanding with 320 grit between coats.

	Thinning ratio %	Nozzle	Air pressure	Coating pressure
Conventional gun	0-10	2-2.2	3 - 4	--
Airless	0-6	11-13	-	80-120
Air mix	0-6	11-13	0.5-1	80-120

General remarks

- Mix well before use.
- **Color matching:** colorants YXP.1139-Colors or YXP.1100-Colors up 6%.
To get transparent / light colors: use YOxx.1061.609AUS as base.
To get dark colors: use clear bases YW.1135US (35 sheen) or YW.1138US (60 sheen)
To get intermediate colors: use white base YO30.1061.02US.
* Clear and white base are miscible.
- If properly stored at temperatures between 5°C/41°F and 35°C/95°F, shelf life is 12 months.
- On application the temperature of the product, the substrate, the coating and the working environment should never fall below 15°C/59°F. Coatings applied at lower temperatures will show chemical and mechanical properties lower than standard performances that can be normally achieved.
- Coating leftovers (washing waters, waters from spray booths, used coatings) must be disposed of according to local regulations. Never dispose residues directly into drains.
- Application tools must be cleaned with water after use.