SOURCE: MSC.197(80).pdf
out, details of the repairs effected should be reported by making specific reference to relevant items in the numbered list.
4.2 Repairs carried out should be reported with identification of:
.1 compartment;
.2 structural member;
.3 repair method (i.e. renewal or modification), including:
.3.1 steel grades and scantlings (if different from the original);
.3.2 sketches/photos, as appropriate;
.4 repair extent; and
.5 non-destructive tests (NDT).
4.3 For repairs not completed at the time of survey, condition of class/recommendation should be imposed with a specific time limit for the repairs. In order to provide correct and proper information to the surveyor attending for survey of the repairs, condition of class/recommendation should be sufficiently detailed with identification of each item to be repaired. For identification of extensive repairs, reference may be given to the survey report.
RESOLUTION MSC.197(80)
(adopted on 20 May 2005)
AMENDMENTS TO THE GUIDELINES ON THE ENHANCED PROGRAMME OF INSPECTIONS DURING SURVEYS OF BULK CARRIERS AND OIL TANKERS (RESOLUTION A.744(18), AS AMENDED)General particulars
Ship's name:
Port of registry :
Deadweight

---CHUNK---

SOURCE: MSC.197(80).pdf
(adopted on 20 May 2005)
AMENDMENTS TO THE GUIDELINES ON THE ENHANCED PROGRAMME OF INSPECTIONS DURING SURVEYS OF BULK CARRIERS AND OIL TANKERS (RESOLUTION A.744(18), AS AMENDED)General particulars
Ship's name:
Port of registry :
Deadweight
(metric tonnes):
Date of build :
- 70-
ANNEX 9
CONDITION EVALUATION REPORT
Issued upon completion of renewal survey
Class/Administration identity number:
Previous class/Administration identity number(s):
IMOnumber :
National flag:
Previou s national flag(s):
Gross tonnage:
National:
ITC (1969):
Classification notation:
Date of major conversion :
Type of conversion: Owner:
Previous owner(s):

1 The survey reports and documents listed below have been reviewed by the undersigned and found to be satisfactory.
2 The renewal survey has been completed in accordance with the present Guideline s on (date) ....
Condition evaluation report Name Title
completed by Signature
Office Date
Condition evaluation report Name Title
completed by Signature
Office Date
Attached report s and documents:
RESOLUTION MSC.197(80)
(adopted on 20 May 2005)
AMENDMENTS TO THE GUIDELINES ON THE ENHANCED

---CHUNK---

SOURCE: MSC.197(80).pdf
completed by Signature
Office Date
Condition evaluation report Name Title
completed by Signature
Office Date
Attached report s and documents:
RESOLUTION MSC.197(80)
(adopted on 20 May 2005)
AMENDMENTS TO THE GUIDELINES ON THE ENHANCED
PROGRAMME OF INSPECTIONS DURING SURVEYS OF BULK CARRIERS AND OIL TANKERS (RESOLUTION A.744(18), AS AMENDED)- 71 -
Contents of condition evaluation report
Part 1 - General particulars:
Part 2 - Report review:
Part 3 - Close-up survey:
Part 4 - Cargo and ballast
piping system:
Part 5 - Thickness measurements:
Part 6 - Tank corrosion
prevention system:
Part 7 - Repairs:
Part 8 - Condition of class/
flag State requirements:
Part 9 - Memoranda:
Part 10 - Conclusion:
See front page
Where and how survey was done
Extent (which tanks)
Examined
Operationally tested
Reference to thickness measurement report
Summary of where measured
Separate form indicating the spaces with
substantial corrosion, and corresponding:
- thickness diminution
- corrosion pattern

Separate form indicating:
- location of coating/anodes
- condition of coating (if applicable)
Identification of tanks/areas
- Acceptable defects

---CHUNK---

SOURCE: MSC.197(80).pdf
substantial corrosion, and corresponding:
- thickness diminution
- corrosion pattern
Separate form indicating:
- location of coating/anodes
- condition of coating (if applicable)
Identification of tanks/areas
- Acceptable defects
- Any points of attention for future surveys,
e.g. for suspect areas
Extended annuaVintermediate survey due to
coating breakdown
Statement on evaluation/verification of
survey report
Extract of thickness measurements
Reference is made to the thickness measurements report :
Position of substantiaUy Thickness Corros ion Remarks: corroded tanks /areas! or (e.g. reference to
areas with deep pitting3 diminution (%) pattern' attached sketches)
RESOLUTION MSC.197(80)
(adopted on 20 May 2005)
AMENDMENTS TO THE GUIDELINES ON THE ENHANCED
PROGRAMME OF INSPECTIONS DURING SURVEYS OF BULK CARRIERS
AND OIL TANKERS (RESOLUTION A.744(18), AS AMENDED)-72-
Notes:
I Substantial corrosion, i.e. 75%-100% of acceptable margins wasted.
2 P = Pitting
C Corrosion in general
3 Any bottom plating with a pitting intensity of 20% or more, with wastage in the
substantial corrosion range or having an average depth of pitting of 1/3 or more of

---CHUNK---

SOURCE: MSC.197(80).pdf
2 P = Pitting
C Corrosion in general
3 Any bottom plating with a pitting intensity of 20% or more, with wastage in the
substantial corrosion range or having an average depth of pitting of 1/3 or more of
actual plate thicknes s should be noted .
Tank corrosion prevention system
Tank Nos.' Tank corrosion Coating condition' Remarks
prevention system2
Notes:
All segregated ballast tanks and combined cargolballast tanks should be listed.
2 C = Coating
A = Anodes

NP = No protection
3 Coating condition according to the following standard:
GOOD
FAIR
POOR
condition with only minor spot rusting.
condition with local breakdown of coating at edges of stiffeners and weld connections and/or light rusting over 20% or more of areas under consideration, but less than as defined for POOR condition.
condition with general breakdown of coating over 20% or more of areas or hard scale at 10% or more of areas under consideration.
If coating condition "POOR " is given, extended annual surveys should be introduced .
This should be noted in part 8 of the contents of the condition evaluation report .

---CHUNK---

SOURCE: MSC.197(80).pdf
or hard scale at 10% or more of areas under consideration.
If coating condition "POOR " is given, extended annual surveys should be introduced .
This should be noted in part 8 of the contents of the condition evaluation report .
Evaluation result oflongitudinal strength of the hull girder of oil tankers of 130 m in length and upwards and of over 10 years of age
(of sections 1,2 and 3 below, only one applicable section should be completed)