2
.

6
5
.
2
T
h
e

l
i
f
e
j
a
c
k
e
t

Vest-type lifejacket Yoke or over-the-head-type lifejacket
C - Cylinder
125 mm diameter for adult sizes
50 mm diameter for infant and child sizes
L - Test load
Figure 1 – Body strength test arrangement for lifejackets
RESOLUTION MSC.200(80)
(adopted on 13 May 2005)
ADOPTION OF AMENDMENTS TO THE REVISED
RECOMMENDATION ON TESTING OF
LIFE-SAVING APPLIANCESMSC 80/24/Add.1
ANNEX 17
Page 5

Dimensions in mm

Size

A B C D E F G H J
Adult 610 114 76.2 127 381 432 508 25.4 178
Child 508 102 76.2 102 279 330 406 22.2 152
Infant 305 63.5 38.1 63.5 191 203 241 19.1 76.2

Figure 2 – Test form for shoulder lift test for lifejackets

RESOLUTION MSC.200(80)
(adopted on 13 May 2005)
ADOPTION OF AMENDMENTS TO THE REVISED
RECOMMENDATION ON TESTING OF

---CHUNK---

SOURCE: MSC.200(80).pdf
Infant 305 63.5 38.1 63.5 191 203 241 19.1 76.2

Figure 2 – Test form for shoulder lift test for lifejackets

RESOLUTION MSC.200(80)
(adopted on 13 May 2005)
ADOPTION OF AMENDMENTS TO THE REVISED
RECOMMENDATION ON TESTING OF
LIFE-SAVING APPLIANCESMSC 80/24/Add.1
ANNEX 17
Page 6

I:\MSC\80\24-ADD-1.DOC

Vest-type lifejacket Yoke or over-the-head-type lifejacket

C - Cylinder
125 mm diameter for adult sizes
50 mm diameter for infant and child sizes
L - Test load

Figure 3 – Shoulder lift test arrangement for lifejackets

2.6 Tests for lifejacke t buoyancy material

The following tests should be carried out on eight specimens of each lifejacket buoyancy material. The specimens should be at least 300 mm square and be of the same thickness as used in the lifejacket. In the case of kapok, the entir e lifejacket should be subjected to the test. The dimensions should be recorded at the beginning and en d of these tests. Where multiple layers of materials are used to achieve the total thickness desired for the lifejacket, the specimens should be of the thinnest material used.

Test for stability under temperature cycling

---CHUNK---

SOURCE: MSC.200(80).pdf
Where multiple layers of materials are used to achieve the total thickness desired for the lifejacket, the specimens should be of the thinnest material used.

Test for stability under temperature cycling

2.6.1 Six specimens should be subjected to temperature cycling as prescribed in 1.2.1.

2.6.2 The dimensions of the specimens (except kapok) should be recorded at the end of the last cycle. The specimens should be carefully examined and should not show any sign of external change of structure or of mechanical qualities.

2.6.3 Two of the specimens should be cut open and should not show any sign of internal change of structure.

2.6.4 Four of the specimens should be used for compression and water absorption tests, two of which should be so tested after they have also been subjected to the diesel oil test as prescribed in 1.4.

Tests for compression and water absorption

2.6.5 The tests should be carried out in fresh water and the specimens should be

---CHUNK---

SOURCE: MSC.200(80).pdf
two of which should be so tested after they have also been subjected to the diesel oil test as prescribed in 1.4.

Tests for compression and water absorption

2.6.5 The tests should be carried out in fresh water and the specimens should be immersed for a period of seven days under a 1.25 m head of water.

2.6.6 The tests should be carried out:

.1 on two specimens as supplied;

.2 on two specimens which have been subj ected to the temperature cycling as prescribed in 2.6.1; and

.3 on two specimens which have been subj ected to the temperature cycling as prescribed in 2.6.1 followed by the diesel oil test as prescribed in 1.4.

2.6.7 The results should state the buoyant for ce in N which each specimen exerts when submerged in water after one and seven da ys' immersion. The reduction of buoyancy should not exceed 10% for specimens which have been exposed to the diesel oil conditioning and must not exceed 5% for al l other specimens. The specimens should show no sign of damage such as shrinking, cracking, swelling, dissolution or change of mechanical qualities.