.2 Freeboard: The average results for clea rance of the mouth above the water for all subjects should not be less than the average for the appropriate size RTD;

.3 Torso angle: The average of all subjects' results should be not less than the average for the appropriate size RTD minus 10°;

.4 Faceplane (head) angle: The average of all subjects' results should be not less than the average for the appropriate size RTD minus 10°; and

.5 Mobility: Mobility of the subject both in and out of the water should be given consideration in determining the acceptability of a device for approval and should be compared to mobility when wearing the appropriate size RTD when climbing out of the water, going up and down stairs, picking up an article from the floor, and then drinking from a cup.

2.9.3 With the exception of reducing freeboard and self-righting performance, the requirements for infant lifejackets may be relaxed if necessary in order to:

.1 contribute to the rescue of the infant by a caretaker;

---CHUNK---

SOURCE: MSC.200(80).pdf
2.9.3 With the exception of reducing freeboard and self-righting performance, the requirements for infant lifejackets may be relaxed if necessary in order to:

.1 contribute to the rescue of the infant by a caretaker;

.2 allow the infant to be fastened to a caretaker and contribute to keeping the infant close to the caretaker;

.3 keep the infant dry, with free respiratory passages;

.4 protect the infant against bumps an d jolts during the evacuation; and

.5 allow a caretaker to monitor and control heat loss by the infant.

2.10 Tests for inflatable lifejackets

2.10.1 Inflation tests

2.10.1.1 Two inflatable lifejackets should be subjected to the temperature cycling test prescribed in 1.2.1 in the uninflated conditi on and should then be externally examined. The inflatable lifejacket materials should s how no sign of damage such as shrinking, cracking, swelling, dissolutio n or change of mechanical qualities. The automatic and manual inflation systems should each be te sted immediately after each temperature cycling test as follows:

.1 After a high temperature cycle, th e two inflatable lif ejackets should be

---CHUNK---

SOURCE: MSC.200(80).pdf

manual inflation systems should each be te sted immediately after each temperature cycling test as follows:

.1 After a high temperature cycle, th e two inflatable lif ejackets should be taken from the stowage temperature of +65°C. One should be activated using the automatic inflation system by placing it in seawater at a temperature of +30°C and the other should be activated using the manual inflation system. Each should fully inflate.

.2 After a low temperature cycle, the two inflatable lifejackets should be taken from the stowage temperature of -30°C. One should be activated using the automatic inflation system by placing it in seawater at a

temperature of -1°C and the other should be activated using the manual inflation system. Each should fully inflate.

2.10.1.2 After exposure to a temperature of - 15°C for a period of at least 8 h, two lifejackets should be activated using the manual inflation system and should fully inflate.

---CHUNK---

SOURCE: MSC.200(80).pdf
inflation system. Each should fully inflate.

2.10.1.2 After exposure to a temperature of - 15°C for a period of at least 8 h, two lifejackets should be activated using the manual inflation system and should fully inflate.

2.10.1.3 After exposure to a temper ature of +40°C for a period of at least 8 h, two lifejackets should be activated using the manual inflation system and should fully inflate.

2.10.2 The test in 2.7 should be conducted using lifejackets both in the inflated and uninflated conditions.

2.10.3 The tests in 2.8 should be conducted using lifejackets that have been inflated both automatically and manually, and also with one of the compartments uninflated. The tests with one of the compartments uninflated should be repeated as many times as necessary to perform the test once with each compartment in the uninflated condition.

2.10.4 Tests of materials for inflatable bladders, inflation systems and components

The material used for the inflatable bladder, inflation system and components should be tested to establish that they are rot-proof, co lour fast and resistant to deterioration from

---CHUNK---

SOURCE: MSC.200(80).pdf

The material used for the inflatable bladder, inflation system and components should be tested to establish that they are rot-proof, co lour fast and resistant to deterioration from exposure to sunlight and that they are not duly affected by seawater, oil or fungal attack.

2.10.4.1 Material tests

Resistance to rot and illumination test ed according to AATCC Method 30:1981 and ISO 105-B04:1988 Illumination should take place to class 4-5.

Following exposure to rot or illumination te sts above the tensile strength should be measured using the grab method given in IS O 5082. Minimum tensile strength should be not less than 300 N per 25 mm in the warp and weft direction.

2.10.4.2 Coated fabrics

Coated fabrics used in the construction of inflatable buoyancy chambers should comply with the following requirements:

.1 Coating adhesion should be tested in accordance with ISO 2411:1991 using the method described in paragraph 5.1 at 100 mm/min and should be not less than 50 N per 50 mm width.

.2 Coating adhesion should be tested when wet following ageing according to ISO 188 with an exposure of 336 0.5 h in fresh water at (70 1) °C,

---CHUNK---

SOURCE: MSC.200(80).pdf
not less than 50 N per 50 mm width.

.2 Coating adhesion should be tested when wet following ageing according to ISO 188 with an exposure of 336 0.5 h in fresh water at (70 1) °C,
following which the method at ISO 2411:1991, paragraph 5.1 should be applied at 100 mm/min and should not be less than 40 N per 50 mm width.

.3 Tear strength should be tested in accordance with ISO 4674:1977 using method A1 and should not be less than 35 N.

.4 Resistance to flex cracking shou ld be tested in accordance with ISO 7854:1984 method A using 9000 flex cycles, there should be no visible cracking or deterioration.

.5 Breaking strength should be tested in accordance with ISO 1421:1977 using the constant-rate-of-extension (CRE) or constant-rate-of-traverse (CRT) method, following conditioning for 24 0.5 h at room temperature

and should not be less than 200 N per 50 mm width.

.6 Breaking strength should be tested in accordance with ISO 1421:1977

---CHUNK---

SOURCE: MSC.200(80).pdf
(CRT) method, following conditioning for 24 0.5 h at room temperature and should not be less than 200 N per 50 mm width.

.6 Breaking strength should be tested in accordance with ISO 1421:1977 using the CRE or CRT method, followi ng conditioning immersed in fresh water for 24 0.5 h at room temperature and should not be less than 200 N per 50 mm width.

.7 Elongation to break should be te sted in accordance with ISO 1421:1977 using the CRE or CRT method following conditioning at room temperature for 24 0.5 h and should not be more than 60%.

.8 Elongation to break should be te sted in accordance with ISO 1421:1977 using the CRE or CRT method followi ng conditioning immersed in fresh water at room temperature for 24 0.5 h and should not be more than 60%.