2.1 Dew point is the temperature at which air is saturated with moisture.

2.2 DFT is dry film thickness.

2.3 Dust is loose particle matter present on a su rface prepared for painting, arising from blast-cleaning or other surface preparation pro cesses, or resulting fr om the action of the environment.

2.4 Edge grinding is the treatment of edge before secondary surface preparation.

2.5 GOOD condition is the condition with minor spot rust ing as defined in the Guidelines on the enhanced programme of inspections dur ing surveys of bulk carriers and oil tankers (resolution A.744(18)).

2.6 Hard coating is a coating that chemically converts during its curing process or a non-convertible air drying coating which may be used for maintenance purposes. It can be either inorganic or organic.

2.7 NDFT is the nominal dry film thickness. 90/10 practice means that 90% of all thickness

---CHUNK---

SOURCE: MSC.244(83).pdf
non-convertible air drying coating which may be used for maintenance purposes. It can be either inorganic or organic.

2.7 NDFT is the nominal dry film thickness. 90/10 practice means that 90% of all thickness measurements should be greater than or equal to NDFT and none of the remaining 10% measurements should be below 0.9 x NDFT.

2.8 Primer coat is the first coat of the coating syst em applied in the shipyard after shop primer application.

2.9 Shop primer is the prefabrication primer coating applied to steel plates, often in automatic plants (and before the first coat of a coating system).

2.10 Stripe coating is painting of edges, weld s, hard to reach areas, etc., to ensure good paint adhesion and proper paint thickness in critical areas.

2.11 Target useful life is the target value, in years, of the durability for which the coating system is designed.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10

---CHUNK---

SOURCE: MSC.244(83).pdf

system is designed.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10
Page 3

I:\MSC\83\28-Add-2.doc
2.12 Technical Data Sheet is paint manufacturers Product Data Sheet which contains detailed technical instruction and information relevant to the coating and its application.

2.13 Totally enclosed space is a space which has no means of access and no ventilation.

2.14 Void space is an enclosed space below the bulkh ead deck, within and forward of, the cargo area of oil tankers or the cargo length area of bulk carriers, excluding:

.1 a dedicated seawater ballast tank;

.2 a space for the carriage of cargo;

.3 a space for the storage of any substance (e.g., oil fuel, fresh water, provisions);

.4 a space for the installation of any mach inery (e.g., cargo pump, ballast pump, bow thruster);

.5 any space in normal use by personnel; and

.6 a double-side skin space of bulk carrier s of 150 m in length and upwards which shall comply with the Performance standa rd for dedicated seawater ballast tanks

---CHUNK---

SOURCE: MSC.244(83).pdf
thruster);

.5 any space in normal use by personnel; and

.6 a double-side skin space of bulk carrier s of 150 m in length and upwards which shall comply with the Performance standa rd for dedicated seawater ballast tanks
in all types of ships and double-side skin spaces of bulk carriers adopted by resolution MSC.215(82).

For the purpose of this regulation, cargo ar ea and cargo length area are as defined in resolution A.744(18).

3 GENERAL PRINCIPLES

3.1 The ability of the coating system to reach its target useful life depends on the type of coating system, steel preparation, application and coating inspecti on and maintenance. All these aspects contribute to the good performance of the coating system.

3.2 Inspection of surface preparation and coating processes should be agreed upon between

the shipowner, the shipyard and the coating manufacturer and presented to the Administration for review. Clear evidence of these inspections shou ld be reported and be included in the Coating Technical File (CTF) (see paragraph 3.4).

3.3 When considering the standard provided in section 4, the following s hould be taken into account:

---CHUNK---

SOURCE: MSC.244(83).pdf
review. Clear evidence of these inspections shou ld be reported and be included in the Coating Technical File (CTF) (see paragraph 3.4).

3.3 When considering the standard provided in section 4, the following s hould be taken into account:

.1 it is essential that specifications, proce dures and the various different steps in the coating application process (including, but not limited to, surface preparation) are strictly applied by the shipbuilder in or der to prevent premature decay and/or deterioration of the coating system;

.2 the coating performance can be improved by adopting measures at the ship design stage such as reducing scallops, using rolled profiles, avoiding complex geometric configurations and ensuring that the struct ural configuration permits easy access for tools and to facilitate cleaning, drainage and drying of the space to be coated; and

---CHUNK---

SOURCE: MSC.244(83).pdf
RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10
Page 4

I:\MSC\83\28-Add-2.doc
.3 the coating performance standa rd provided in this resolution is based on the experience of manufacturers, shipyards an d ship operators; it is not intended to exclude suitable alternative coating systems, providing a performance at least equivalent to that specified in this Standard is demonstrated. Acceptance criteria for alternative systems are provided in section 8.

3.4 Coating Technical File

3.4.1 Specification of the coating system applied to void spaces in bulk carriers and oil tankers, records of the shipyards and shipowners coati ng work, detailed criteria for coating selection, job specifications, insp ection, maintenance and repair should be documented in the Coating Technical File (CTF), which should be reviewed by the Administration or an organization recognized by the Administration.

3.4.2 New construction stage

The Coating Technical File should contain at least the following ite ms relating to this Standard

---CHUNK---

SOURCE: MSC.244(83).pdf
recognized by the Administration.

3.4.2 New construction stage

The Coating Technical File should contain at least the following ite ms relating to this Standard and should be delivered by the shipyard at the new ship construction stage:

.1 copy of Statement of Compliance or Type Approval Certificate;

.2 copy of Technical Data Sheet, including: