.1 product name and identification mark and/or number;
.2 materials, components and composition of the coating system, colours;
.3 minimum and maximum dry film thickness;
.4 application methods, tools and/or machines;
.5 condition of surface to be coated (d e-rusting grade, cleanness, profile, etc.); and
.6 environmental limitations (temperature and humidity);

.3 shipyard work records of coating application, including:

.1 applied actual space and area (in square metres) of each void space;
.2 applied coating system;
.3 time of coating, thickness, number of layers, etc.;
.4 ambient condition during coating; and
.5 method of surface preparation;

.4 procedures for inspection a nd repair of coating system during ship construction;

---CHUNK---

SOURCE: MSC.244(83).pdf
.3 time of coating, thickness, number of layers, etc.;
.4 ambient condition during coating; and
.5 method of surface preparation;

.4 procedures for inspection a nd repair of coating system during ship construction;

.5 coating log issued by the coating inspector , stating that the coating was applied in accordance with the specifica tions to the satisfaction of the coating supplier representative and specifying deviations from the specifications (example of daily log and non-conformity report, see annex 2);

.6 shipyards verified insp ection report, including:

.1 completion date of inspection;
.2 result of inspection;
.3 remarks (if given);
.4 inspector signature; and

.7 procedures for in-servi ce maintenance and repair of coating system.
RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10
Page 5

I:\MSC\83\28-Add-2.doc
3.4.3 Maintenance, repair and partial re-coating

Maintenance, repair and partial re-coating activitie s should be recorded in the Coating Technical

---CHUNK---

3.4.3 Maintenance, repair and partial re-coating

Maintenance, repair and partial re-coating activitie s should be recorded in the Coating Technical File in accordance with the relevant section of the guidelines for coating maintenance and repair1.

3.4.4 Re-coating

If full re-coating is carried out, the items specified in paragra ph 3.4.2 should be r ecorded in the Coating Technical File.

3.4.5 The Coating Technical File should be kept on board and maintained throughout the life of the ship.

3.5 Health and safety

The shipyard is responsible for the implementati on of national regulations to ensure the health and safety of individuals and to minimize the risk of fire and explosion.

4 COATING STANDARD

4.1 Performance standard

This Standard is based on specifications and requirements which intend to provide a target useful coating life of 15 years, which is considered to be th e time period, from initial application, over which the coating system is intended to remain in GOOD condition. The actual useful life will

---CHUNK---

SOURCE: MSC.244(83).pdf
coating life of 15 years, which is considered to be th e time period, from initial application, over which the coating system is intended to remain in GOOD condition. The actual useful life will vary, depending on numerous variables including actual conditions encountered in service.

4.2 Standard application

4.2.1 Protective coatings for the following void sp aces should comply with the requirements in this Standard:

.1 in bulk carriers:

.1 double bottom pipe passages / pipe tunnels;

.2 small void spaces located behind gusset or shedder plates at the bottom of corrugation bulkheads with the exception of totally enclosed spaces;

.3 other small void spaces in cargo spaces, with the exception of totally enclosed spaces;

.4 lower transverse stool of transver se bulkheads, with the exception of totally enclosed spaces2; and

.5 upper transverse stool of transverse bulkheads, with the exception of totally enclosed spaces2; and

1 To be developed by the Organization.
2 Noting, inter alia, the mandatory provisions of resolution A.744(18), as amended, regarding the requirement to

---CHUNK---

SOURCE: MSC.244(83).pdf
totally enclosed spaces2; and

1 To be developed by the Organization.
2 Noting, inter alia, the mandatory provisions of resolution A.744(18), as amended, regarding the requirement to undertake close-up surveys of the internal structure of upper and lower stools, where fitted.

.2 in oil tankers:

.1 forward cofferdam/cofferdam separating cargo from forepeak;

.2 cofferdam in cargo area/cofferdam separating incompatible cargoes;

.3 aft cofferdam;

.4 duct keel/pipe tunnels;

.5 lower bulkhead stools; and

.6 upper bulkhead stools.

4.2.2 Protective coatings for the following void sp aces should comply with the requirements in the Performance standard for protective coatings fo r dedicated seawater ballast tanks in all types of ships and double-side skin spaces of bulk carriers (resolution MSC.215(82)):

.1 in bulk carriers:

---CHUNK---

SOURCE: MSC.244(83).pdf
the Performance standard for protective coatings fo r dedicated seawater ballast tanks in all types of ships and double-side skin spaces of bulk carriers (resolution MSC.215(82)):

.1 in bulk carriers:

.1 double-side skin spaces in ships of less than 150 m in length; and

.2 upper and lower side void spaces and double bottoms void spaces in cargo area; and

.2 in oil tankers:

double-side skin (DSS) voids including sides, bottoms/double hull voids spaces protecting cargo oil tanks.

4.2.3 No requirements are contained in this Standard for protecti ve coatings for the following void spaces in bulk carriers and oil tankers:

.1 totally enclosed spaces located behind gusset or shedder plates at the bottom of corrugation bulkheads and other small totally enclosed spaces in cargo tanks;

.2 lower transverse stool of transverse bu lkheads that are totally enclosed spaces;

.3 upper transverse stool of transverse bul kheads that are totally enclosed spaces;