.4 transducer voids; and

.5 any spaces not specifically mentioned in paragraphs 4.2.1 and 4.2.2.

4.3 Special application

---CHUNK---

SOURCE: MSC.244(83).pdf
.3 upper transverse stool of transverse bul kheads that are totally enclosed spaces;

.4 transducer voids; and

.5 any spaces not specifically mentioned in paragraphs 4.2.1 and 4.2.2.

4.3 Special application

4.3.1 This Standard covers protectiv e coating requirements for the sh ip steel structure. It is noted that other independent items are fitted within the tanks to which coatings are applied to provide protection against corrosion.

4.3.2 It is recommended that this Standard be appl ied, to the extent possibl e, to those portions of permanent means of access provided for inspection, not integral to the ship structure, such as rails, independent platforms, ladders, etc. Other equivalent methods of providing corrosion protection for non-integral items may also be us ed, provided they do not impair the performance of the coatings of the surrounding structure. Access arrangements that are integral to the ship

---CHUNK---

SOURCE: MSC.244(83).pdf
protection for non-integral items may also be us ed, provided they do not impair the performance of the coatings of the surrounding structure. Access arrangements that are integral to the ship structure, such as incr eased stiffener depths for walkways, stringers, etc., should fully comply with this Standard.

4.3.3 It is also recommended that supports for piping, measuring devices, etc., be coated in accordance with the provisions for non-integral items indicated in paragraph 4.3.2.

4.4 Basic coating requirements

4.4.1 The requirements for protective coating systems, which should be applied at ship construction to void spaces in bulk carriers and oil tankers meeting the standard specified in paragraph 4.1, are listed in table 1.

4.4.2 Coating manufacturers should provide a specification of the protective coating system to satisfy the requirements of table 1.

4.4.3 The Administration or an organization rec ognized by the Administration should verify the Technical Data Sheet and Statement of Compliance or Type Approval Certificate for the protective coating system.

4.4.4 The shipyard should apply th e protective coating in acco rdance with the verified

---CHUNK---

SOURCE: MSC.244(83).pdf
Technical Data Sheet and Statement of Compliance or Type Approval Certificate for the protective coating system.

4.4.4 The shipyard should apply th e protective coating in acco rdance with the verified Technical Data Sheet and its own verified application procedures.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10
Page 8

I:\MSC\83\28-Add-2.doc

Table 1 - Basic coating system requirements for void spaces in bulk carriers and oil tankers

Characteristic	Requirement
1 Design of coating system	
.1 Selection of the coating system	The selection of the coating system should be considered by the parties involved with respect to the service conditions and planned maintenance. The following aspects, among other things should be considered: .1 location of space relati ve to heated surfaces; .2 required surface conditions; .3 required surface cleanliness and dryness; .4 relative humidity; .5 access and maintenance; and .6 mechanical ventilation. Coating manufacturers should have products with documented

---CHUNK---

SOURCE: MSC.244(83).pdf
.2 required surface conditions;
.3 required surface cleanliness and dryness;
.4 relative humidity;
.5 access and maintenance; and
.6 mechanical ventilation.

Coating manufacturers should have products with documented

satisfactory performance records a nd technical data sheets. The manufacturers should also be capable of rendering adequate technical assistance. Performance records, Technical Data Sheet and technical assistance (if given) should be recorded in the Coating Technical File.

Coatings for application underneath sun-heated decks or on bulkheads forming boundaries of heated spaces should be able to withstand repeated heating and/or cooling without becoming brittle.

.2 Coating type Epoxy-based systems.

Other coating systems with performa nce according to the test procedure in annex 1.

When a multi-coat system is applied, contrasting colour is recommended for each coat.

The top coat should be of a light colour in order to faci litate in-service inspection.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE

---CHUNK---

SOURCE: MSC.244(83).pdf
for each coat.

The top coat should be of a light colour in order to faci litate in-service inspection.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE

Characteristic Requirement
.3 Coating pre-qualification test
Epoxy-based systems tested prior to the date of a doption of this standard in a laboratory by a method corres ponding to the test procedure in annex 1 or equivalent, which, as a minimum, meets the requirements for rusting and blistering may be accepted;

or any coating system which meets th e requirements in table 1.1.3 of the Performance standard for protectiv e coating for dedicated seawater ballast tanks in all types of ships and double-side skin spaces of bulk carriers (resolution MSC.215(82)), is accepted and may be applied in accordance with this Standard;

or which have documented field e xposure for 5 years with a final coating condition of not less than GOOD may also be accepted.

For other systems, including epo xy-based systems tested after the

---CHUNK---

SOURCE: MSC.244(83).pdf
accordance with this Standard;

or which have documented field e xposure for 5 years with a final coating condition of not less than GOOD may also be accepted.

For other systems, including epo xy-based systems tested after the adoption of this Standard, testing ac cording to the procedure in annex 1 to this Standard should be required.

.4 Job
specification
There should be a minimum of one st ripe coat and one spray coat. The stripe coat should be ap plied on thermally cut free edges and small holes only.