Surface contaminants such as rust, greas e, dust, salt, oil, etc., should be removed prior to painting with proper methods according to the paint manufacturers recommendation. Abra sive inclusions embedded in the coating should be removed. Job specifications should include the dry-to-recoat times and walk-on time given by the manufacturer.

.5 NDFT (nominal total dry film thickness)3
NDFT 200 µm with a 90/10 rule for epoxy based coatings, other systems to coating manufacturers specifications.

Maximum total dry film thickness acco rding to manufacturers detailed specifications.

---CHUNK---

SOURCE: MSC.244(83).pdf
total dry film thickness)3
NDFT 200 µm with a 90/10 rule for epoxy based coatings, other systems to coating manufacturers specifications.

Maximum total dry film thickness acco rding to manufacturers detailed specifications.

Care should be taken to avoid increa sing the thickness in an exaggerated way. Wet film thickness should be regularly checked during application.

Thinner should be limited to those types and quantities recommended by the manufacturer.

3 Type of gauge and calibration in accordance with SSPC-PA2:2004. Paint Application Specification No.2.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10
Page 10

I:\MSC\83\28-Add-2.doc
Characteristic Requirement
2 PSP (Primary surface preparation)
.1 Blasting and profile4,5 Sa 2½; with profiles between 30-75 µm.
Blasting should not be carried out when:

.1 the relative humidity is above 85%; or
.2 the surface temperature of steel is less than 3°C above the dew point.

---CHUNK---

SOURCE: MSC.244(83).pdf
.1 Blasting and
profile4,5 Sa 2½; with profiles between 30-75 µm.
Blasting should not be carried out when:

.1 the relative humidity is above 85%; or
.2 the surface temperature of steel is less than 3°C above the dew
point.

Checking of the steel surface cleanliness and roughness profile should be
carried out at the end of the surface preparation and before the application
of the primer, in accordance with the manufacturers recommendations.

.2 Water soluble
salt limit
equivalent to
NaCl6
50 mg/m2 of sodium chloride.

.3 Shop primer Zinc containing inhibitor free zinc silicate based or equivalent.

Compatibility with main coating system should be confirmed by the
coating manufacturer.

3 SSP (Secondary surface preparation)
.1 Steel condition The steel surface should be prepared so that the coating selected can
achieve an even distribution at the required NDFT and have an adequate
adhesion by removing sharp edges, grinding weld beads and removing
weld spatter and any other surface contaminant7.

Edges to be smooth, subject to one pa ss grinding or at least equivalent
process before painting8.

---CHUNK---

SOURCE: MSC.244(83).pdf
weld spatter and any other surface contaminant7.

Edges to be smooth, subject to one pa ss grinding or at least equivalent
process before painting8.

4 Reference standard: ISO 8501-1:1988/Suppl:1994. Preparation of steel substrate before application of paints and related products Visual assessment of surface cleanliness.

5 Reference standard: ISO 8503-1/2:1988. Preparation of steel substrate before application of paints and related products Surface roughness characteristics of blast-cleaned steel substrates.

6 Conductivity measured in accordance with ISO 8502-9:1998. Preparation of steel substrate before application of paints and related products Test for the assessment of surface cleanliness.

7 Reference standard: ISO 8501-3:2001 (grade P1). Preparat ion of steel substrate before application of paints and related products Visual assessment of surface cleanliness.

8 Reference standard: ISO 8501-3:2001 (grade P2). Preparat ion of steel substrate before application of paints and related products Visual assessment of surface cleanliness.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)

---CHUNK---

SOURCE: MSC.244(83).pdf
8 Reference standard: ISO 8501-3:2001 (grade P2). Preparat ion of steel substrate before application of paints and related products Visual assessment of surface cleanliness.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10
Page 11

I:\MSC\83\28-Add-2.doc
Characteristic Requirement
.2 Surface
treatment4 For damaged shop primer:
Sa 2 or St 3 on damaged shop primer and welds;

For intact shop primer:

Sa 2 removing at least 70% of intact shop primer, which has not passed a pre-qualification certified by test procedures in table 1.1.3.

If the complete coating system comprising epoxy-based main coating and shop primer has passed a pre-qualificatio n certified by test procedures in table 1.1.3 intact shop primer may be retained provided the same epoxy coating system is used. The retained shop primer should be cleaned by sweep blasting, high pressure water washing or other methods in accordance with the manufacturers recommendation.

If a zinc silicate shop primer has passed the pre-qualification test of

---CHUNK---

SOURCE: MSC.244(83).pdf
sweep blasting, high pressure water washing or other methods in accordance with the manufacturers recommendation.

If a zinc silicate shop primer has passed the pre-qualification test of table 1.1.3 as part of an epoxy coa ting system, it may be used in combination with other epoxy coatings certified under table 1.1.3, provided that the compatibility has been confirmed by the manufacturer by the test in accordance with paragraph 1.7 of appendix 1 to annex 1 of the Performance standard for protective coatings for dedicated seawater

ballast tanks in all types of ships and double-side skin spaces of bulk carriers, without wave movement.

.3 Surface treatment after erection[4]	St 3 or better or Sa 2 where practicable on butts and damages. Coating in overlap to be feathered.
.4 Profile requirements[5]	In case of full or partial blasting 30-75 µm, otherwise as recommended by the coating manufacturer.
.5 Dust	9 Dust quantity rating 2 for dust size class 3, 4 and 5.
.6 Water soluble salts limit equivalent to NaCl after blasting/ grinding[6]	100 mg/m2 of sodium chloride.