.7 Oil
contamination
No oil contamination.

---CHUNK---

SOURCE: MSC.244(83).pdf
.5 Dust 9 Dust quantity rating 2 for dust size class 3, 4 and 5.

.6 Water soluble
salts limit
equivalent to
NaCl after
blasting/
grinding6
100 mg/m2 of sodium chloride.

.7 Oil
contamination
No oil contamination.

9 Reference standard: ISO 8502-3:1993. Preparation of steel substrate before application of paints and related products Test for the assessment of surface cleanliness.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10
Page 12

I:\MSC\83\28-Add-2.doc
Characteristic Requirement
4 Miscellaneous
.1 Ventilation Adequate ventilation is nece ssary for the proper drying and curing of coating. Ventilation should be ma intained throughout the application process and for a period after applic ation is completed, as recommended by the coating manufacturer.

.2 Environmental
conditions
Coating should be applied under controlled humidity and surface conditions, in accordance with the manufacturers specifications. In

---CHUNK---

SOURCE: MSC.244(83).pdf
by the coating manufacturer.

.2 Environmental
conditions
Coating should be applied under controlled humidity and surface

conditions, in accordance with the manufacturers specifications. In addition, coating should not be applied when:

.1 the relative humidity is above 85%; or
.2 the surface temperature is less than 3°C above the dew point.

.3 Testing of
coating3 Destructive testing should be avoided.
Dry film thickness should be measured after each coat for quality control purposes and the total dry film thickness should be confirmed after completion of final coat, using appropriate thickness gauges.

.4 Repair Any defective areas, e.g. pin-holes, bubbles, voids, etc. should be marked up and appropriate repa irs effected. All such repairs should be re-checked and documented.

5 COATING SYSTEM APPROVAL

Results from prequalification tests (table 1.1.3) of the coating system should be documented, and a Statement of Compliance or T ype Approval Certificate should be issued if found satisfactory by a third party, independent of the coating manufacturer.

6 COATING INSPECTION REQUIREMENTS

6.1 General

---CHUNK---

SOURCE: MSC.244(83).pdf
a Statement of Compliance or T ype Approval Certificate should be issued if found satisfactory by a third party, independent of the coating manufacturer.

6 COATING INSPECTION REQUIREMENTS

6.1 General

6.1.1 To ensure compliance with this Standard, the following should be carried out by qualified coating inspectors certified to NACE Coating Insp ector Level 2, FROSIO Inspector level III or equivalent as verified by the Administration10.

6.1.2 Coating inspectors should inspect surface preparation and coating application during the coating process by carrying out, as a minimum, t hose inspection items identified in section 6.2 to ensure compliance with this Standard. Emphasis should be placed on initiation of each stage of surface preparation and coatings application, as im proper work is extremely difficult to correct later in the coating progress. Representative structural memb ers should be non-destructively

10 In accordance with SOLAS regulation I/6, for the purposes of this Standard, the Administration may entrust a

---CHUNK---

SOURCE: MSC.244(83).pdf
10 In accordance with SOLAS regulation I/6, for the purposes of this Standard, the Administration may entrust a recognized organization acting on its behalf to determine compliance with the provisions of this Standard.

examined for coating thickness. The inspector shoul d verify that appropriate collective measures have been carried out.

6.1.3 Results from the inspection should be recorded by the inspector and should be included in the CTF (refer to annex 2, Example of Daily Log and Non-conformity Report).

6.2 Inspection items

Construction stage	Inspection items
	1 The surface temperature of steel, th e relative humidity and the dew point should be measured and recorded before the blasting process starts and at times of sudden changes in weather.
	2 The surface of steel plates should be test ed for soluble salt checked for oil, grease and other contamination.

---CHUNK---

SOURCE: MSC.244(83).pdf
should be measured and recorded before the blasting process starts and at times of sudden changes in weather.

2 The surface of steel plates should be test ed for soluble salt checked for oil, grease and other contamination.

	3 The cleanliness of the steel surface should be monitored in the shop primer application process.
Primary surface preparation	4 The shop primer material should be c onfirmed to meet the requirements of 2.3 of table 1.
Thickness	If compatibility with the main co ating system has been declared, then the thickness and curing of the zinc silicate shop primer should be confirmed to conform to the specified values.
	1 After completing construc tion of the block and be fore secondary surface preparation starts, a visual inspection for steel surface treatment including edge treatment should be carried out.

Any oil, grease or other visible contamination should be removed.

2 After blasting/grinding/cleaning and prio r to coating, a visual inspection of the prepared surface should be carried out.

On completion of blasting and cleaning and prior to the application of the

---CHUNK---

SOURCE: MSC.244(83).pdf
2 After blasting/grinding/cleaning and prio r to coating, a visual inspection of the prepared surface should be carried out.

On completion of blasting and cleaning and prior to the application of the first coat of the system, the steel su rface should be tested for levels of remaining soluble salts in at least one location per block.

3 The surface temperature, the relati ve humidity and the dew point should be monitored and recorded during the coating application and curing.

4 Inspection should be performed of th e steps in the coating application process mentioned in table 1.

Block
assembly