---CHUNK---

SOURCE: MSC.244(83).pdf
Water 40 ± 2 ° C
Test panels
Room temperature 23 ± 2 ° C
100 % RH

Figure 1: Condensation chamber

3.2 Test results

3.2.1 Prior to the testing, the following measured data of the coating system should be reported:

.1 infrared (IR) identification of the base and hardener components of the coating;

.2 specific gravity 11, of the base and hardener components of the paint; and

.3 number of pinholes, low voltage detector at 90 V.

3.2.2 After the testing, the followi ng measured data should be reported:

.1 blisters and rust 12;

.2 dry film thickness (DFT) (use of a template);

.3 adhesion value 13; and

.4 flexibility 14 modified according to panel thickness (3 mm steel, 300 µm coating, 150 mm cylindrical mandrel gives 2% elongation) for information only.

11 According to ISO 2811-74.
12 According to ISO 4628/2 and ISO 4628/3.
13 According to ISO 4624.
14 According to ASTM D4145.

---CHUNK---

SOURCE: MSC.244(83).pdf
14 According to ASTM D4145.

RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE

3.3 Acceptance criteria

3.3.1 The test results based on section 2 should satisfy the following criteria:

Item	Acceptance criteria for epoxy-based systems applied according to table 1 of this standard	Acceptance criteria for alternative systems
Blisters on panel	No blisters	No blisters
Rust on panel	Ri 0 (0%)	Ri 0 (0%)
Number of pinholes	0	0
Adhesive failure	> 3.5 MPa	
Adhesive failure between substrate and coating or between coats for 60% or more of the areas	> 5 MPa	
Adhesive failure between substrate and coating or between coats for 60% or more of the areas		
Cohesive failure	> 3 MPa	
Cohesive failure in coating for 40% or more of the area		
	> 5 MPa	
Cohesive failure in coating for 40% or more of the area		

3.3.2 Epoxy-based systems tested pr ior to the date of adoption of this Standard should satisfy only the criteria for blistering and rust in the table above.

---CHUNK---

SOURCE: MSC.244(83).pdf
> 5 MPa

Cohesive failure in coating for
40% or more of the area

3.3.2 Epoxy-based systems tested pr ior to the date of adoption of this Standard should satisfy

only the criteria for blistering and rust in the table above.

3.3.3 Epoxy-based systems tested when applied ac cording to table 1 of this Standard should satisfy the criteria for epoxy-based systems as indicated in the table above.

3.3.4 Alternative systems not n ecessarily epoxy-based and/or not necessarily applied according to table 1 of this Standard should satisfy the cr iteria for alternative systems as indicated in the table above.

3.4 Test report

The test report should include the following information:

.1 name of the manufacturer;

.2 date of tests;

.3 product name/identification of both paint and primer;

.4 batch number;

.5 data of surface preparation on st eel panels, including the following:

.1 surface treatment;
.2 water soluble salts limit;

---CHUNK---

.5 data of surface preparation on st eel panels, including the following:

.1 surface treatment;
.2 water soluble salts limit;
.3 dust; and
.4 abrasive inclusions;

.6 application data of coati ng system, including the following:

.1 shop primed;
.2 number of coats;
.3 recoat interval 15;
.4 dry film thickness (DFT) prior to testing 15;

.5 thinner 15;
.6 humidity 15;
.7 air temperature 15; and
.8 steel temperature;

.7 test results accord ing to section 2; and

.8 judgment according to section 3.

15 Both of actual specimen data and manufacturers requirement/recommendation.

ANNEX 2

EXAMPLE OF DAILY LOG AND NON-CONFORMITY REPORT