INTERNATIONAL LRIT DATA EXCHANGE
ON AN INTERIM BASISRESOLUTION MSC.243(83)
(adopted on 12 October 2007)
ESTABLISHMENT OF INTERNATIONAL LRIT DATA EXCHANGE
ON AN INTERIM BASIS
---CHUNK---
SOURCE: MSC.244(83).pdf
RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
I:\MSC\83\28-Add-2.doc
ANNEX 10
RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE COATINGS
FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS
THE MARITIME SAFETY COMMITTEE,
RECALLING Article 28(b) of the Convention on the International Maritime Organization concerning the functions of the Committee,
HAVING ADOPTED, by resolution MSC.215( 82), the Performance standard for protective coatings for dedicated seawater ballast tanks in all types of ships and double-side skin
spaces of bulk carriers and, by resolution MSC. 216(82), amended SOLAS regulation II-1/3-2 to make the performance standard mandatory;
RECOGNIZING the need to also develop a perf ormance standard for protective coatings for void spaces on bulk carriers and oil tankers,
HAVING CONSIDERED, at its ei ghty-third session, the pro posed Performance standard for protective coatings for void spaces on bulk carriers and oil tankers,
---CHUNK---
SOURCE: MSC.244(83).pdf
for void spaces on bulk carriers and oil tankers,
HAVING CONSIDERED, at its ei ghty-third session, the pro posed Performance standard for protective coatings for void spaces on bulk carriers and oil tankers,
1. ADOPTS the Performance standard for protective coatings for void spaces on bulk carriers and oil tankers, the text of which is set out in the Annex to the present resolution;
2. INVITES Member Governments to utilize the Performance standard when applying protective coatings to void spaces on bulk carriers and oil tankers.
RESOLUTION MSC.244(83)
(adopted on 5 October 2007)
ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE
COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2
ANNEX 10
Page 2
I:\MSC\83\28-Add-2.doc
ANNEX
PERFORMANCE STANDARD FOR PROTECTIVE COATINGS FOR VOID SPACES
ON BULK CARRIERS AND OIL TANKERS
1 PURPOSE
This Standard provides technical requirements for protective coatings for void spaces construct ed
of steel in bulk carriers and oil tankers.
2 DEFINITIONS
For the purpose of this Standard, the following definitions apply:
---CHUNK---
SOURCE: MSC.244(83).pdf
1 PURPOSE
This Standard provides technical requirements for protective coatings for void spaces construct ed
of steel in bulk carriers and oil tankers.
2 DEFINITIONS
For the purpose of this Standard, the following definitions apply:
2.1 Dew point is the temperature at which air is saturated with moisture.
2.2 DFT is dry film thickness.
2.3 Dust is loose particle matter present on a su rface prepared for painting, arising from blast-cleaning or other surface preparation pro cesses, or resulting fr om the action of the environment.
2.4 Edge grinding is the treatment of edge before secondary surface preparation.
2.5 “ GOOD” condition is the condition with minor spot rust ing as defined in the Guidelines on the enhanced programme of inspections dur ing surveys of bulk carriers and oil tankers (resolution A.744(18)).
2.6 Hard coating is a coating that chemically converts during its curing process or a non-convertible air drying coating which may be used for maintenance purposes. It can be eithe r
inorganic or organic.
2.7 NDFT is the nominal dry film thickness. 90/10 practice means that 90% of all thickness
---CHUNK---

SOURCE: MSC.244(83).pdf
non-convertible air drying coating which may be used for maintenance purposes. It can be eithe
r
inorganic or organic.
2.7 NDFT is the nominal dry film thickness. 90/10 practice means that 90% of all thickness
me