ot be accessible.

***

RESOLUTION MSC.243(83)

(adopted on 12 October 2007)

ESTABLISHMENT OF INTERNATIONAL LRIT DATA EXCHANGE

ON AN INTERIM BASISRESOLUTION MSC.243(83)

(adopted on 12 October 2007)

ESTABLISHMENT OF INTERNATIONAL LRIT DATA EXCHANGE

ON AN INTERIM BASIS

-

RESOLUTION MSC.244(83)

(adopted on 5 October 2007)

ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE

COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS MSC 83/28/Add.2

I:\MSC\83\28-Add-2.doc

ANNEX 10

RESOLUTION MSC.244(83)

(adopted on 5 October 2007)

ADOPTION OF PERFORMANCE STANDARD FOR PROTECTIVE COATINGS

FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS

THE MARITIME SAFETY COMMITTEE,

RECALLING Article 28(b) of the Convention on the International Maritime Organization

concerning the functions of the Committee,

HAVING ADOPTED, by resolution MSC.215( 82), the Performance standard for

protective coatings for dedicated seawater ballast tanks in all types of ships and double-side skin

spaces of bulk carriers and, by resolution MSC. 216(82), amended SOLAS regulation II-1/3-2 to

make the performance standard mandatory;

RECOGNIZING the need to also develop a perf ormance standard for protective coatings

for void spaces on bulk carriers and oil tankers,

HAVING CONSIDERED, at its ei ghty-third session, the pro posed Performance standard

for protective coatings for void spaces on bulk carriers and oil tankers,

-

for void spaces on bulk carriers and oil tankers,

HAVING CONSIDERED, at its ei ghty-third session, the pro posed Performance standard

for protective coatings for void spaces on bulk carriers and oil tankers,

1. ADOPTS the Performance standard for protective coatings for void spaces on bulk

carriers and oil tankers, the text of which is set out in the Annex to the present resolution;

2. INVITES Member Governments to utilize the Performance standard when applying

protective coatings to void spaces on bulk carriers and oil tankers.

RESOLUTION MSC.244(83)

(adopted on 5 October 2007)

ANNEX

PERFORMANCE STANDARD FOR PROTECTIVE COATINGS FOR VOID SPACES ON BULK CARRIERS AND OIL TANKERS

1 PURPOSE

This Standard provides technical requirements for protective coatings for void spaces constructed of steel in bulk carriers and oil tankers.

2 DEFINITIONS

For the purpose of this Standard, the following definitions apply:

-

1 PURPOSE

This Standard provides technical requirements for protective coatings for void spaces constructed of steel in bulk carriers and oil tankers.

2 DEFINITIONS

For the purpose of this Standard, the following definitions apply:

2.1 Dew point is the temperature at which air is saturated with moisture.

2.2 DFT is dry film thickness.

2.3 Dust is loose particle matter present on a su rface prepared for painting, arising from blast-cleaning or other surface preparation pro cesses, or resulting fr om the action of the environment.

2.4 Edge grinding is the treatment of edge before secondary surface preparation.

2.5 “ GOOD” condition is the condition with minor spot rust ing as defined in the Guidelines on the enhanced programme of inspections dur ing surveys of bulk carriers and oil tankers (resolution A.744(18)).

2.6 Hard coating is a coating that chemically converts during its curing process or a non-convertible air drying coating which may be used for maintenance purposes. It can be either inorganic or organic.

2.7 NDFT is the nominal dry film thickness. 90/10 practice means that 90% of all thickness

-

non-convertible air drying coating which may be used for maintenance purposes. It can be either inorganic or organic.

2.7 NDFT is the nominal dry film thickness. 90/10 practice means that 90% of all thickness measurements should be greater than or equal to NDFT and none of the remaining 10% measurements should be below 0.9 x NDFT.

2.8 Primer coat is the first coat of the coating syst em applied in the shipyard after shop primer application.

2.9 Shop primer is the prefabrication primer coating applied to steel plates, often in

automatic

plants (and before the first coat of a coating system).

2.10 Stripe coating is painting of edges, weld s, hard to reach areas, etc., to ensure good paint

adhesion and proper paint thickness in critical areas.

2.11 Target useful life is the target value, in years, of the durability for which the coating

system is designed.