




Mercury Intrusion Measurements



Modal Diameter	22,3	nm
Median Diameter (50%)	19,4	nm
Porosity	51,3	%
Pore Volume	0,479	cm ³ g ⁻¹


Leipzig, 13.02.2020:

Bastian Oberleiter

Bastian Oberleiter



Mercury Intrusion Measurements



Modal Diameter	4,5	nm
Median Diameter (50%)	4,7	nm
Porosity	54,1	%
Pore Volume	0,535	cm³g⁻¹

Leipzig, 13.02.2020:

Bastian Oberleiter

Bastian Oberleiter