



# A4009MFN1325

HDPE for Textile

**A4009MFN1325** is a high density polyethylene homopolymer with a narrow molecular weight distribution primarily intended for the extrusion of monofilaments.

**A4009MFN1325** has the following characteristics:

- High tenacity monofilaments & tapes
- Very low gels content
- Superior processability & surface quality
- Very low MVTR (Moisture Vapour Transmission Rate)

Examples of applications:

- Extrusion of monofilaments
- High tenacity tapes
- Cereal liners
- Injection moulding

## TYPICAL PHYSICAL PROPERTIES

Property	Typical Value	Units	Test Method
Melt flow rate (2.16 kg load)	0.9	g/10min	ISO 1133 Cond. D
Density	960	kg/m <sup>3</sup>	ISO 1872/1
Tensile strength at yield	30	MPa	ISO 527-2
Tensile strength at break	22	MPa	ISO 527-2
Elongation at break	> 500	%	ISO 527-2
Flexural Modulus	1100	MPa	ISO 178

The properties shown are typical values measured on the product and should not be considered as specifications



## High Density Polyethylene



### Food contact applications

As dispatched from our plants Innovene grades meet the requirements of most countries in respect of their usage in food contact applications. Official confirmation of compliance with current requirements in the individual countries will be provided on request. No liability can be accepted for any damage, loss, or injury arising out of failure to obtain such confirmation, or failure to observe any recommendations given.

### Polyethylene and the environment

"INEOS will act responsibly and caringly towards those who work for us, the community whom we serve and the environment in which we live."

Natural Innovene polymers, as supplied, can be recycled, incinerated or disposed of in landfill without detriment to the environment.

With recycling, clean waste can be reused for many less demanding applications.

Alternatively, with properly controlled and efficient incineration, preferably linked to heat or other energy recovery systems, polyethylene's high calorific value will assist the combustion of municipal solid waste.

In landfill sites, Innovene grades do not degrade to produce voids, and do not emit dangerous gases or contribute to ground water pollution.

Natural Innovene polymers, as manufactured, comply with the limit for heavy metals (100 ppm total of lead, cadmium, mercury and hexavalent chromium) in packaging materials as defined in the European Union Directive 94/62/EC on packaging and packaging waste and the corresponding US CONEG regulations.

If pigments or other additives are incorporated into the Innovene polymers at the processing stage, the above statements may not be fully valid. INEOS will be pleased to offer advice in specific cases.

### Health and safety

Material Safety Data Sheets for Innovene grades are available, and should be consulted before handling and using Innovene grades.

### Exclusion of liability

Information contained in this publication, while accurate to the best knowledge and belief of INEOS and its subsidiary companies ("INEOS"), is not intended and should not be construed as a warranty or representation for which INEOS assumes any legal responsibility.

Any information or advice obtained from INEOS otherwise than by means of this publication and whether relating to INEOS materials or other materials, is also given in good faith. However, it remains at all times the responsibility of the customer to ensure that INEOS materials are suitable for the particular purpose intended.

In so far as materials not manufactured or supplied by INEOS are used in conjunction with or instead of INEOS materials, the customer should ensure he has received from the manufacturer or supplier all technical data and other information relating to such materials.

INEOS accepts no liability whatsoever (except as otherwise expressly provided by law) arising out of the use of information supplied, the application, adaptation or processing of the products described herein, the use of other materials in lieu of INEOS materials or the use of INEOS materials in conjunction with such other materials.

In particular, INEOS accepts no liability for infringement of patents of third parties arising out of the application or adaptation of information or advice obtained from INEOS in this publication or otherwise.

The information provided in this datasheet is intended to assist you in the use of INEOS materials. It does not attempt to describe every possible condition of use of INEOS materials.

INEOS

