

(19) United States

(12) Patent Application Publication (10) Pub. No.: US 2024/0213517 A1 **MARUYAMA**

Jun. 27, 2024 (43) **Pub. Date:**

(54) NON-AQUEOUS RECHARGEABLE **BATTERY AND METHOD FOR** MANUFACTURING NON-AQUEOUS RECHARGEABLE BATTERY

(71) Applicants: PRIMEARTH EV ENERGY CO., LTD., Kosai-shi (JP); TOYOTA JIDOSHA KABUSHIKI KAISHA, Tokyo-shi (JP); PRIME PLANET **ENERGY & SOLUTIONS, INC.,** Tokyo (JP)

(72) Inventor: Shunya MARUYAMA, Toyohashi-shi (JP)

(73) Assignees: PRIMEARTH EV ENERGY CO., LTD., Kosai-shi (JP); TOYOTA JIDOSHA KABUSHIKI KAISHA, Toyota-shi (JP); **PRIME PLANET ENERGY & SOLUTIONS, INC.,** Tokyo (JP)

(21) Appl. No.: 18/393,337 (22)Filed: Dec. 21, 2023

(30)Foreign Application Priority Data

(JP) 2022-207954 Dec. 26, 2022

Publication Classification

(51) Int. Cl. H01M 10/04 (2006.01)

U.S. Cl. (52)CPC H01M 10/045 (2013.01); H01M 10/0459 (2013.01); **H01M 10/0468** (2013.01)

(57)**ABSTRACT**

A non-aqueous rechargeable battery includes an electrode body formed by rolling a stack of positive and negative electrode plates with a separator that holds a non-aqueous electrolyte solution disposed in between. The electrode body includes a curved portion in which layers of the electrode body are curved. The positive electrode plate includes a foil of a positive electrode substrate and a positive electrode mixture layer applied to the positive electrode substrate. The negative electrode plate includes a foil of a negative electrode substrate and a negative electrode mixture layer applied to the negative electrode substrate. The negative electrode mixture layer includes a negative electrode active material that intercalates a charge carrier during charging. A coefficient of static friction between the negative electrode mixture layer and the separator is 0.60 or greater. A coefficient of static friction between the positive electrode mixture layer and the separator is 0.50 or less.

