

(19) United States

(12) Patent Application Publication (10) Pub. No.: US 2024/0213105 A1

Jun. 27, 2024 (43) **Pub. Date:**

(54) MITIGATING SURFACE DAMAGE OF PROBE PADS IN PREPARATION FOR DIRECT BONDING OF A SUBSTRATE

(71) Applicant: ADEIA SEMICONDUCTOR BONDING TECHNOLOGIES INC..

San Jose, CA (US)

(72) Inventors: Guilian Gao, San Jose, CA (US);

Laura Wills Mirkarimi, Sunol, CA (US); Gaius Gillman Fountain, JR.,

Youngsville, NC (US)

Appl. No.: 18/600,278

Filed: Mar. 8, 2024

Related U.S. Application Data

- (63) Continuation of application No. 17/825,240, filed on May 26, 2022, now Pat. No. 11,978,681, which is a continuation of application No. 16/845,913, filed on Apr. 10, 2020, now Pat. No. 11,355,404.
- (60) Provisional application No. 62/837,004, filed on Apr. 22, 2019.

Publication Classification

(51) Int. Cl. H01L 21/66 (2006.01)H01L 21/768 (2006.01) H01L 23/522 (2006.01)H01L 23/532 (2006.01)H01L 23/538 (2006.01)

(52) U.S. Cl.

CPC H01L 22/34 (2013.01); H01L 21/7685 (2013.01); H01L 21/76877 (2013.01); H01L 23/5226 (2013.01); H01L 23/53238 (2013.01); H01L 23/53266 (2013.01); H01L 23/5386 (2013.01)

(57)ABSTRACT

Mitigating surface damage of probe pads in preparation for direct bonding of a substrate is provided. Methods and layer structures prepare a semiconductor substrate for direct bonding processes by restoring a flat direct-bonding surface after disruption of probe pad surfaces during test probing. An example method fills a sequence of metals and oxides over the disrupted probe pad surfaces and builds out a dielectric surface and interconnects for hybrid bonding. The interconnects may be connected to the probe pads, and/or to other electrical contacts of the substrate. A layer structure is described for increasing the yield and reliability of the resulting direct bonding process. Another example process builds the probe pads on a next-to-last metallization layer and then applies a direct bonding dielectric layer and damascene process without increasing the count of mask layers. Another example process and related layer structure recesses the probe pads to a lower metallization layer and allows recess cavities over the probe pads.



