US 20230231139A1

(19) **United States**

(12) **Patent Application Publication** (10) **Pub. No.: US 2023/0231139 A1**

LI et al. (43) **Pub. Date: Jul. 20, 2023**

(54) **BINDER, NEGATIVE-ELECTRODE SLURRY, NEGATIVE ELECTRODE, AND LITHIUM-ION BATTERY**

(71) Applicants: **Envision Dynamics Technology (Jiangsu) Co., Ltd.**, Jiangsu (CN); **ENVISION RUITAI DYNAMICS TECHNOLOGY (SHANGHAI) CO.,LTD.**, Shanghai (CN)

(72) Inventors: **Ruonan LI**, Shanghai (CN); **Huayu SUN**, Shanghai (CN)

(73) Assignees: **Envision Dynamics Technology (Jiangsu) Co., Ltd.**, Jiangsu (CN); **Envision Intelligent Innovation Dynamics Technology (Shanghai) Ltd.**, Shanghai (CN)

(21) Appl. No.: **18/009,989**

(22) PCT Filed: **Feb. 8, 2021**

(86) PCT No.: **PCT/CN2021/076032**

§ 371 (c)(1),
(2) Date: **Dec. 13, 2022**

(30) **Foreign Application Priority Data**

Jan. 28, 2021 (CN) 202110117295.0

Publication Classification

(51) **Int. Cl.**

H01M 4/62	(2006.01)
H01M 10/0525	(2006.01)
H01M 4/04	(2006.01)
H01M 4/583	(2006.01)

(52) **U.S. Cl.**

CPC ***H01M 4/622*** (2013.01); ***H01M 10/0525*** (2013.01); ***H01M 4/0404*** (2013.01); ***H01M 4/583*** (2013.01); *H01M 2004/027* (2013.01)

(57) **ABSTRACT**

The present application discloses a binder, a negative-electrode slurry, a negative electrode, and a lithium-ion battery. In the present application, the binder comprises a first block polymer and a second block polymer. The first block polymer is a lithiated tetrablock polymer having a structure shown as B-C-B-A, wherein A represents a polymer block A, B represents a polymer block B, and C represents a polymer block C; the polymer block A is polymerized from alkenyl formic acid monomers; the polymer block B is polymerized from aromatic vinyl monomers; and the polymer block C is polymerized from acrylate monomers. The second block polymer is a lithiated triblock polymer having a structure shown as E-F-E, wherein E represents a polymer block E, and F represents a polymer block F; the polymer block E is polymerized from alkenyl formic acid monomers; and the polymer block F is polymerized from acrylate monomers.