US 20240213447A1

(19) United States

(12) Patent Application Publication (10) Pub. No.: US 2024/0213447 A1

DEGUCHI (43) Pub. Date: Jun. 27, 2024

(54) **POSITIVE ELECTRODE PLATE FOR NON-AQUEOUS ELECTROLYTE RECHARGEABLE BATTERY, NON-AQUEOUS ELECTROLYTE RECHARGEABLE BATTERY, AND METHOD FOR MANUFACTURING POSITIVE ELECTRODE PLATE FOR NON-AQUEOUS ELECTROLYTE RECHARGEABLE BATTERY**

(71) Applicants: **PRIMEARTH EV ENERGY CO., LTD.**, Kosai-shi, Shizuoka (JP); **TOYOTA JIDOSHA KABUSHIKI KAISHA**, Toyota-shi, Aichi-ken (JP); **PRIME PLANET ENERGY & SOLUTIONS, INC.**, Tokyo (JP)

(72) Inventor: **Shotaro DEGUCHI**, Toyohashi-shi (JP)

(73) Assignees: **PRIMEARTH EV ENERGY CO., LTD.**, Kosai-shi, Shizuoka (JP); **TOYOTA JIDOSHA KABUSHIKI KAISHA**, Toyota-shi, Aichi-ken (JP); **PRIME PLANET ENERGY & SOLUTIONS, INC.**, Tokyo (JP)

(21) Appl. No.: **18/231,169**

(22) Filed: **Aug. 7, 2023**

(30) **Foreign Application Priority Data**

Aug. 10, 2022 (JP) 2022-128380

Publication Classification

(51) **Int. Cl.**

H01M 4/139	(2010.01)
H01M 4/04	(2006.01)
H01M 4/62	(2006.01)
H01M 10/0525	(2010.01)
H01M 4/02	(2006.01)

(52) **U.S. Cl.**

CPC ***H01M 4/139*** (2013.01); ***H01M 4/0404*** (2013.01); ***H01M 4/0471*** (2013.01); ***H01M 4/625*** (2013.01); ***H01M 10/0525*** (2013.01); *H01M 2004/021* (2013.01); *H01M 2004/028* (2013.01)

(57) **ABSTRACT**

A positive electrode plate for a non-aqueous electrolyte rechargeable battery includes a positive electrode mixture layer that is formed by a positive electrode mixture including a positive electrode active material and a conductive material. When $R_S=(R_C\times B_C)/(R_A\times B_A)$ is satisfied, where R_C (mass %) represents a percentage of the conductive material, B_C (m^2/g) represents a specific surface area of the conductive material, R_A (mass %) represents a percentage of the positive electrode active material, B_A (m^2/g) represents a specific surface area of the positive electrode active material, and R_S represents a total surface area ratio, an aspect ratio AR of the conductive material is thirty or greater, the total surface area ratio R_S is in a range of 0.20 to 1.93, and a porosity P (%) of the positive electrode mixture layer is in a range of 40% to 55%.