US 20240213545A1

(19) United States

(12) Patent Application Publication (10) Pub. No.: US 2024/0213545 A1

Koide et al. (43) Pub. Date: Jun. 27, 2024

(54) BIPOLAR LEAD-ACID STORAGE BATTERY

(71) Applicants: **The Furukawa Battery Co., Ltd.**, Yokohama (JP); **Furukawa Electric Co., Ltd.**, Tokyo (JP)

(72) Inventors: **Ayano Koide**, Iwaki (JP); **Keizo Yamada**, Iwaki (JP)

(21) Appl. No.: **18/424,076**

(22) Filed: **Jan. 26, 2024**

Related U.S. Application Data

(63) Continuation of application No. PCT/JP2022/029008, filed on Jul. 27, 2022.

(30) **Foreign Application Priority Data**

Jul. 28, 2021 (JP) 2021-123478

Publication Classification

(51) **Int. Cl.**

H01M 10/18	(2006.01)
H01M 4/02	(2006.01)
H01M 4/14	(2006.01)
H01M 4/68	(2006.01)
H01M 50/477	(2006.01)

(52) **U.S. Cl.**

CPC ***H01M 10/18*** (2013.01); ***H01M 4/14*** (2013.01); ***H01M 4/685*** (2013.01); ***H01M 50/477*** (2021.01); *H01M 2004/021* (2013.01); *H01M 2004/029* (2013.01)

(57) **ABSTRACT**

In a bipolar lead-acid storage battery including a main substrate in which cell members are individually accommodated in spaces, a positive electrode current collector plate is disposed on one surface of the main substrate, and a negative electrode current collector plate is disposed on the other surface of the main substrate, the corrosion of the thin-formed positive electrode current collector plate is prevented to extend a life of the bipolar lead-acid storage battery. A thickness (T1) of a positive electrode current collector plate disposed on one surface of a main substrate, which is a substrate disposed between adjacent cell members, ranges from 0.15 mm to 0.75 mm. A ratio (T1/T2) of the thickness (T1) of the positive electrode current collector plate relative to the thickness (T2) of a negative electrode current collector plate disposed on another face of the main substrate ranges from 1.5 to 6.5.