



US 20240237541A1

(19) **United States**

(12) **Patent Application Publication**
Arimoto et al.

(10) **Pub. No.: US 2024/0237541 A1**

(43) **Pub. Date: Jul. 11, 2024**

(54) **ORGANIC PIEZOELECTRIC FILM**

Publication Classification

(71) Applicant: **DAIKIN INDUSTRIES, LTD.**, Osaka (JP)

(72) Inventors: **Masaharu Arimoto**, Osaka (JP); **Saori Sakami**, Osaka (JP); **Tetsuhiro Kodani**, Osaka (JP); **Takashi Kanemura**, Osaka (JP)

(73) Assignee: **DAIKIN INDUSTRIES, LTD.**, Osaka (JP)

(21) Appl. No.: **18/604,797**

(22) Filed: **Mar. 14, 2024**

Related U.S. Application Data

(63) Continuation of application No. PCT/JP2022/034620, filed on Sep. 15, 2022.

Foreign Application Priority Data

Sep. 16, 2021 (JP) 2021-150967

(51) **Int. Cl.**

H10N 30/857 (2023.01)

C08L 27/16 (2006.01)

C08L 27/18 (2006.01)

H10N 30/098 (2023.01)

H10N 35/01 (2023.01)

(52) **U.S. Cl.**

CPC **H10N 30/857** (2023.02); **C08L 27/16**

(2013.01); **C08L 27/18** (2013.01); **H10N**

30/098 (2023.02); **H10N 35/01** (2023.02);

C08L 2201/10 (2013.01); **C08L 2203/16**

(2013.01); **C08L 2203/20** (2013.01)

(57)

ABSTRACT

An object is to provide an organic piezoelectric film with a high level of piezoelectricity and a high level of transparency. The organic piezoelectric film of the present disclosure has a total light transmittance of 90% or more, an internal haze value of 0.2%/μm or less per unit film thickness or an internal haze value of 4% or less, and piezoelectric constant d_{33} of 10 pC/N or more after heating at 110° C. for 10 minutes.

