Conversion Coatings on Non-Ferrous Metals

Kosta Sergakis[1]

[1]Michigan State University, East Lansing, Michigan

Abstract

In engineering and manufacturing, non-ferrous metals like aluminum, magnesium, and zinc are praised for their strength-to-weight ratios and electrical conductivity. However, these materials are chemically active and susceptible to environmental degradation, which can lead to premature failure or loss of mechanical integrity. To ensure long-term durability, industries rely on conversion coatings - thin layers formed by chemical or electrochemical reactions that transform the metal surface into an adherent, insoluble compound. These coatings serve as a critical foundation, providing corrosion resistance and a superior "key" for subsequent paints, sealants, or adhesives.

The Five Primary Conversion Coatings

Chromate Conversion Coatings (CCC) have long served as the benchmark for aerospace and defense due to their unique "active defense" mechanism [Figure 1]. These coatings contain hexavalent chromium [Cr(VI)] species that remain partly soluble within the film; if the surface is damaged, these ions physically migrate to the scratch to repassivate the exposed metal. While this self-healing capability inhibits both anodic and cathodic corrosion reactions effectively, the high toxicity and carcinogenicity of Cr(VI) have forced a significant industrial shift toward trivalent chromium [Cr(III)] and completely chrome-free alternatives.

Anodizing offers a different approach by using an electrochemical process to grow a thick, integrated layer of aluminum oxide directly from the substrate [Figure 2]. Unlike a painted-on coating, this oxide layer is structurally part of the metal and cannot chip or peel. The process creates a highly ordered, porous structure that is ideal for absorbing dyes for aesthetic finishes, though these pores must eventually by "sealed" - often in hot water - to close the surface and maximize its corrosion resistance [1].

For high-volume industries like automotive manufacturing, Zirconium and Titanium Nano-Ceramics have emerged as the leading eco-friendly replacements for traditional toxic pretreatments. These systems operate at room temperature and form ultra-thin inorganic films, typically only 20 to 100 nanometers thick, through the hydrolysis of oxyfluoride species [Figure 3]. Their primary advantage lies in their environmental efficiency, as they produce significantly less hazardous sludge and require less energy than legacy chemical lines.

In applications requiring complex material joining, Silane-Based Treatments function as molecular coupling agents that bridge the gap between inorganic metals and organic topcoats like epoxy [2]. The bonding mechanism is dual-functional: silanol groups form strong covalent Si-O-metal bonds with the substrate, while organic functional groups cross-link directly into the resin of the adhesive or paint.

Finally, Phosphate Conversion Coatings remain a staple for steel and multi-metal pretreatment lines. By chemically converting the surface into a polycrystalline layer of zinc, manganese, or iron phosphate, the process creates a high-surface-area "key" that dramatically improves paint adhesion. Beyond simple corrosion protection, specific variants like manganese phosphate are used on high-friction engine components, such as gears and bearings, to provide essential wear resistance and lubricity during the initial "break-in" period of the machinery.

Figures



Figure 1: CCC Diagram [3]



Figure 2: Anodizing Layer on Aluminum [4]



Figure 3: TEM of Zr Nanoparticles in Nickel Substrate [5]

Conclusion

The selection of a conversion coating is a balance between required performance, environmental compliance, and manufacturing efficiency. While hexavalent chromate remains the unmatched standard for self-healing and structural reliability in aerospace, the global push toward sustainability is rapidly elevating the role of nano-ceramics and silane hybrids. Ultimately, whether through the electrochemical growth of an anodized layer or the molecular bridging of a silane treatment, these conversion processes are the indispensable link that allows non-ferrous metals to survive and thrive in the world's most demanding environments.

Acknowledgement

References

[1] ASM International, *Surface Engineering* (ASM Handbook), 4th. Materials Park, Ohio: ASM International, 2007, vol. 5, ISBN: 9780871703842.

[2] T. S. Narayanan, I.-S. Park, and M.-H. Lee, "Surface modification of magnesium and its alloys for biomedical applications," en, pp. 29–87, 2015. DOI: 10.1016/B978-1-78242-077-4.00002-4. [Online]. Available: https://linkinghub.elsevier.com/retrieve/pii/B9781782420774000024.

[3] Li, Liangliang, "Corrosion protection provided by trivalent chromium process conversion coatings on aluminum alloys," Ph.D. dissertation, Michigan State University. DOI: 10.25335/4KSV-5156. [Online]. Available: https://d.lib.msu.edu/etd/2243.

[4] M. Schneider and W. Fürbeth, "Anodizing—The pore makes the difference," en, *Materials and Corrosion*, vol. 73, no. 11, pp. 1752–1765, Nov. 2022, ISSN: 0947-5117, 1521-4176. DOI: 10.1002/maco.202213324. [Online]. Available: https://onlinelibrary.wiley.com/doi/10.1002/maco.202213324.

[5] M. Zagula-Yavorska, J. Morgiel, J. Romanowska, and J. Sieniawski, "Nanoparticles in zirconium-doped aluminide coatings," en, *Materials Letters*, vol. 139, pp. 50–54, Jan. 2015, ISSN: 0167577X. DOI: 10.1016/j.matlet.2014.09.128. [Online]. Available: https://linkinghub.elsevier.com/retrieve/pii/S0167577X14017753.