

Bureau of Indian Standards

Manak Bhawan, 9, Bahadur Shah Zafar Marg
New Delhi - 110002

IS 17091:2018

2018

FULL GRAIN LEATHER FOR FOOTWEAR

SPECIFICATION

ICS 59.140.30
BIS 2018

Indian Standard

1 SCOPE

This standard specifies requirements for full grain leather used in footwear manufacturing. It covers physical and chemical properties.

2 PHYSICAL REQUIREMENTS

Property	Requirement	Test Method
Tensile Strength	Min 15 N/mm ²	IS 17091 Part 1
Elongation at Break	Min 30%	IS 17091 Part 1
Tear Strength	Min 25 N	IS 17091 Part 2
Flex Resistance	Min 50,000 cycles	IS 17091 Part 3
Colour Fastness to Rubbing	Min 3 (dry), 2 (wet)	IS 17091 Part 4

3 CHEMICAL REQUIREMENTS

Parameter	Requirement
pH Value	3.5-6.0
Chromium(VI) Content	Max 3 mg/kg
Formaldehyde	Max 75 mg/kg
Azodyes (Aromatic Amines)	Max 30 mg/kg