

Veridian Petrochemicals
Bharuch Complex

Document no: INSP-C-1101-THICKNESS-SURVEY Revision: A
Title: Thickness survey of atmospheric column C-1101
Owner: Gopal Iyer
Issued: 06 May 2026

Primary equipment: C-1101, Atmospheric column

Inspector: Gopal Iyer
Equipment: C-1101

Findings. Ultrasonic thickness readings at 48 locations. Minimum measured wall 14.2 mm against a retirement thickness of 11.5 mm. Corrosion rate 0.18 mm per year at the overhead section, remaining life 15 years. Result: satisfactory.