






アノーサイト品とアノーサイトレス品との特性比較

10.4.2012
MARUWA (MALAYSIA)SDN.BHD.

Comparison of Characteristics

Item	Unit	Specification	0.635t Less Anorthite	0.76t Anorthite
Roughness : Ra	μ m	0.2~0.8	0.293	0.273
Specific Gravity	g/cm ³	>3.75	3.766	3.757
Bending Strength	MPa	>380	432	426
Thermal Conductivity	W/mK	>24	24.1	24.5
Composition	MgO	wt%	—	0.67
	Al ₂ O ₃	wt%	96±1	96.97
	SiO ₂	wt%	—	1.93
	CaO	wt%	—	0.55

Surface Condition

Mag.	Surface		Break Surface	
	0.635t Less-Anorthite	0.76t Anorthite	0.635t Less-Anorthite	0.76t Anorthite
x 500				
x2,500				

アノーサイト品とアノーサイトレス品での特性比較において、双方に大差はなく同等の特性値を示していた。