

Soft matter metamaterials

Author: Anja Bregar

Advisor: Miha Ravnik

March 27, 2017

Liquid crystals are soft materials, which in a range of temperatures and molecular concentrations possess a degree of orientational order in contrast to their positional disorder [1]. This is typically achieved by the molecules of liquid crystal being elongated in one direction. They have proven to be an important material in soft matter physics with many possibilities for applications in different industries, notably in liquid crystal displays. Their orientational order is the origin of several other characteristics. One of them is their anisotropic elasticity: the free energy of liquid crystals increases, if – because of external fields or boundary conditions – their orientational order is disturbed. The structural and spatially dependent forces, which arise from that account, generate a plethora of field structures and ordering phenomena. Furthermore, their orientational order implies optical anisotropy [2]: mostly, liquid crystals possess an extraordinary index of refraction (along the long axis of the molecules) larger than the ordinary index. Their optical birefringence is a noteworthy tool in the control of flow-of-light in optical systems. Since liquid crystals are also relatively easily manipulated with external fields, especially electric field, which tends to turn the long axis of the liquid crystal molecules to be polarized along the field, the elastic and optical properties can be well controlled.

Optical metamaterials are another fascinating segment of materials science and are characterised by their extraordinary optical properties [3]. The defining feature of metamaterials is their man-made composition: they are built in periodic unit cells with periodicity generally several times smaller than the wavelength of operating light waves, with the intent of light propagating through the material as if the material was homogeneous. However, since the specific geometric characteristics and the material composition of the periodic building blocks can be adjusted, the optical response of such a composite can be, to an extent, engineered. Since the early 2000s, the field of research has expanded to many different areas of investigation. The central interest at the beginning was to obtain materials which could produce negative refractive index for light in some chosen range of wavelengths, which has been experimentally observed for wavelengths from infrared to optical [4, 5]. With negative-index materials, some attractive applications have been constructed, for instance lenses with subwavelength resolution or invisibility cloaks [6, 7]. But because of the high losses inside metals at optical frequencies and fabrication difficulties, the incentive has lately moved from producing bulk metamaterials with metallic components towards other options, like metamaterials made from dielectrics [8], which have lower losses, and metasurfaces – 2D metamaterials [9]. With metasurfaces, it is possible to

precisely shape the wavefront – design the phase and polarisation – of the transmitted light [9], and use them as selective absorbers. While it is very difficult to construct optically perfectly isotropic metamaterials, the anisotropy has also been exploited in the field of hyperbolic metamaterials [10], which have an anisotropic permittivity tensor with some eigenvalues negative. With it, negative refraction of the Poynting vector can also be achieved without the need for negative permeability.

The fields of liquid crystals and metamaterials are intertwined in a number of experimental and theoretical examples. It is worth mentioning negative refraction is not limited to metamaterials: liquid crystals and other birefringent materials can refract light negatively, when the incoming angle of light is almost perpendicular [11]. Cholesteric liquid crystal films have been used as metasurfaces because of their capability to efficiently control the phase of the transmitted light [12]. Liquid crystals have been used to achieve orientational or even to an extent positional ordering of metamaterial constituent parts: numerous experiments have been performed with golden nanorods ordering because of their prolong shape in connection with the elasticity of liquid crystals [13, 14, 15]. Numerical analysis has suggested that a material composed of metallic spheres, dispersed in liquid crystal, would have the eigenvalues of permittivity tensor differently signed [16, 17]. Some experiments have been performed in that direction as well [18, 19]. Another usage of liquid crystals inside metamaterials was to adjust the metamaterial properties with electric field. With applying voltage, the operational frequency of the metamaterial can be fine-tuned [20, 21], and the liquid crystals can be used to switch between the on- and off-states of a metasurface [22].

Optical propagation through metamaterials is very complicated due to different material effects and elaborate geometry boundary conditions. In liquid crystals, the definite calculation of the flow of light is because of their complicated director field structures equally challenging. With that in mind, numerical simulations are a viable tool in determining the response of such soft matter structures. My thesis will be prepared with a code developed in our group. It is based on FDTD with slight alterations. FDTD (short for finite-difference time-domain) is a finite difference method, where the derivatives are approximated with finite differences, while the time-domain part means a wide range of frequencies can be covered with one simulation. (prehodni pojavi). In FDTD, Maxwell's equations are integrated quite explicitly, which allows for simple implementation of different optical phenomena such as nonlinearity. Traditionally, FDTD is used in combination with Yee mesh, in which the components of electrical and magnetic fields are positioned in a cubic stacked grid and propagated in a leapfrog fashion in time. Our code is adapted for optically anisotropic materials, as well as for frequency dispersive materials with the ADE (auxiliary differential equation) method. As a model for frequency dispersive dielectric function, the plasma, Drude, and Lorentz models can be used. We have also implemented the possibility of anisotropic and frequency dispersive materials in one.

While the main objective of this PhD is to explore the optical response of soft matter metamaterials, it is also crucial to take into account the relaxation of the liquid crystal by optical fields as well. This will be done with free energy minimisation algorithms, namely the

relaxation algorithm [?], also incorporated in our group. The code takes into account different time scales of the light propagation (\approx ps) and relaxation (\approx ms).

With these powerful tools we will examine several theoretical and experimental example cases of soft-matter metamaterials. As a model case we will firstly explore optically anisotropic systems with the eigenvalues of the permittivity tensor with different signs: liquid-crystal like metamaterials. Firstly we will be interested in a case on refraction from vacuum into a system with optical axis homogeneous across the material and tilted with respect to the metamaterial boundary. As an upgrade of this systems, examples with periodic modulation of the director profile will be examined. As a comparison with the already existing cholesteric positive- n systems (the optical axis is twisting in the plane of the incoming plane wave), we will explore cholesteric hyperbolic metamaterial systems with some of the permittivity eigenvalues negative and compare results with the all-positive case. We will be especially interested in the Bragg-reflective regime for circularly polarised light. Additionally, we will perform calculations for the propagation of light perpendicularly to the optical axis, for which no clear theoretical framework is established. If the time will permit, we will exhibit 3D spatial modulation of frequency-dispersive permittivity tensor and explore possibilities for successful modulation of light.

A crucial reason why to control and manipulate light is to guide it. Many different applications, from photonic circuits to waveguides, all designed to convey information, rely on efficient control of light. An compelling option for waveguiding is to enhance their properties with liquid crystals. Liquid crystals can be used as an addition to the existing photonic-crystal-like waveguides [?], where it has been shown they increase the performance of such structure by XX%. If the photonic fibre is filled exclusively with liquid crystal, it can be used as a waveguide as well, since the refractive-index gradient controls the flow-of-light.

The control over the flow of light will be explored for materials with all-positive refractive index as well. In cooperation with prof. Etienne Brasselet from University of Bordeaux, different proposals for waveguides, composed and filled with liquid crystals, will be simulated and analysed theoretically. Through different boundary conditions and other manipulation, different director profiles can be introduced into the liquid crystal. The modulation of the refractive index profile can in turn affect the propagation of light. With some director profiles we can achieve focusing of selected incoming polarizations. Special emphasis will be put on the director profiles which exhibit focusing for positive anisotropy ($n_o < n_e$), so the structures are easily obtainable experimentally.

A way to engineer soft (meta-)materials is to combine liquid crystal with metallic colloids. The elasticity of liquid crystals affects the distribution and arrangement of colloids. The colloidal suspension in liquid crystals have been shown to be ordered because of the elasticity of liquid crystals [?, ?, ?, ?]: Musevic and Smalyukh groups have experimentally shown the elastic forces between the defect structures to be strong enough to achieve orientational ordering of the (spatially anisotropic, i.e. square or triangular) colloids, and also to lower the free energy in such colloidal clusters by arranging. Theoretical work has been done by our group as well [?].

To compose a bulk metamaterial from bottoms up, we would like to test self-assembly of metallic colloids in liquid crystals. As some orientations of the colloid are energetically more favourable because of nematic elastic energy, the horseshoe colloids might, as the theoretical studies of J. Aplinc [?] show, self-assemble in 2D and 3D photonic crystals. The analysis of the interplay between the influences of the geometry of such a photonic crystal and the optical parameters of the materials used provides a rich case of study. Comparison of metallic colloidal inclusions with dielectric ones also gives experimental diversity. Since the optical parameters are highly dependent on the frequency of light, diverse response is achieved across different wavelengths. Experimental realisation of these ideas would be explored in the team of prof. Muševič, group F5 on JSI.

We would like to cooperate with ... (našteješ vse, ki se jih spomniš (??))

References

- [1] P. G. de Gennes and J. Prost, *The Physics of Liquid Crystals, Second Edition*. Oxford University Press, 1995.
- [2] E. Hecht, *Optics*. Addison-Wesley Longman, 2002.
- [3] C. M. Soukoulis and M. Wegener, “Past achievements and future challenges in the development of three-dimensional photonic metamaterials,” *N. Photon.*, vol. 5, pp. 69 – 77, 2011.
- [4] D. R. Smith, W. J. Padilla, D. C. Vier, S. C. Nemat-Nasser, and S. Schultz, “Composite medium with simultaneously negative permeability and permittivity,” *Phys. Rev. Lett.*, vol. 84, 2000.
- [5] J. Valentine, S. Zhang, T. Zentgraf, E. Ulin-Avila, D. A. Genov, G. Bartal, and X. Zhang, “Three-dimensional optical metamaterial with a negative refractive index,” *Nature*, vol. 455, p. 376, 2008.
- [6] M. Khorasaninejad, W. T. Chen, R. C. Devlin, J. Oh, A. Y. Zhu, and F. Capasso, “Metallenses at visible wavelengths: Diffraction-limited focusing and subwavelength resolution imaging,” *Science*, vol. 352, p. 1190, 2016.
- [7] X. Ni, Z. J. Wong, M. Mrejen, Y. Wang, and X. Zhang, “An ultrathin invisibility skin cloak for visible light,” *Science*, vol. 349, p. 1310, 2015.
- [8] S. Jahani and Z. Jacob, “All-dielectric metamaterials,” *Nat. Nanotechnol.*, vol. 11, p. 23, 2016.
- [9] N. Yu and F. Capasso, “Flat optics with designer metasurfaces,” *Nat. Mater.*, vol. 13, p. 139, 2014.

- [10] A. Poddubny, I. Iorsh, P. Belov, and Y. Kivshar, “Hyperbolic metamaterials,” *Nature Photon.*, vol. 7, p. 948, 2013.
- [11] O. P. Pishnyak and O. D. Lavrentovich, “Electrically controlled negative refraction in a nematic liquid crystal,” *Appl. Phys. Lett.*, vol. 89, p. 251103, 2006.
- [12] J. Kobashi, H. Yoshida, and M. Ozaki, “Planar optics with patterned chiral liquid crystals,” *Nature Photon.*, vol. 10, p. 389, 2016.
- [13] H. Park, A. Agarwal, N. A. Kotov, and O. D. Lavrentovich, “Controllable side-by-side and end-to-end assembly of au nanorods by lyotropic chromonic materials,” *Langmuir*, vol. 24, 2008.
- [14] Q. Liu, Y. Cui, D. Gardner, X. Li, S. He, and I. I. Smalyukh, “Self-alignment of plasmonic gold nanorods in reconfigurable anisotropic fluids for tunable bulk metamaterial applications,” *Nano Lett.*, vol. 10, 2010.
- [15] A. B. Golovin and O. D. Lavrentovich, “Electrically reconfigurable optical metamaterial based on colloidal dispersion of metal nanorods in dielectric fluid,” *Applied Physics Letters*, vol. 95, no. 25, p. 254104, 2009.
- [16] D. Jia, C. Yang, X. Li, Z. Peng, Y. Liu, Z. Cao, Q. Mu, L. Hu, D. Li, L. Yao, X. Lu, X. Xiang, H. Zhang, and L. Xuan, “Optical hyperbolic metamaterials based on nanoparticles doped liquid crystals,” *Liq. Cryst.*, vol. 41, p. 207, 2013.
- [17] G. Pawlik, K. Tarnowski, W. Walasik, C. Mitus, and I. Khoo, “Liquid crystal hyperbolic metamaterial for wide-angle negative-positive refraction and reflection,” *Opt. Lett.*, vol. 39, p. 1744, 2014.
- [18] A. Baron, A. Aradian, V. Ponsinet, and P. Barois, “Self-assembled optical metamaterials,” *Optics and Laser Technology*, vol. 82, p. 94, 2016.
- [19] M. Draper, I. M. Saez, S. J. Cowling, P. Gai, B. Heinrich, B. Donnio, D. Guillon, and J. W. Goodby, “Self-assembly and Shape Morphology of Liquid Crystalline Gold Metamaterials,” *Adv. Funct. Mater.*, vol. 21, p. 1260, 2011.
- [20] Q. Zhao, L. Kang, B. Du, J. Zhou, H. Tang, X. Liang, and B. Zhang, “Electrically tunable negative permeability metamaterials based on nematic liquid crystals,” *Appl. Phys. Lett.*, vol. 90, 2007.
- [21] X. Wang, D.-H. Kwon, D. H. Werner, I.-C. Khoo, A. V. Kildishev, and V. M. Shalaev, “Tunable optical negative-index metamaterials employing anisotropic liquid crystals,” *Appl. Phys. Lett.*, vol. 91, p. 143122, 2007.
- [22] O. Buchnev, N. Podoliak, M. Kaczmarek, N. I. Zheludev, and V. A. Fedotov, “Electrically Controlled Nanostructured Metasurface Loaded with Liquid Crystal: Toward Multifunctional Photonic Switch,” *Adv. Opt. Mater.*, vol. 3, p. 674, 2015.