




INSPECTION STANDARD (HT LAB)




☐ Prototype	☐ Pre-Launch	☒ Production	Date (Original)	18/02/2011			
Part Name:- Gear -1st		Part No.:- 2212P05301	Inspection Standard Number	SIP/3020/210			
Customer :- TAFE AGCO		Change Level.:-00	Part Stage	HT Lab.			
Sr.No.	Parameter	Special Char. Class	Methods				Reaction Plan
			Product Specification	Inspection Method	Inspection Frequency	Control Method	
1.	Surface Hardness	*	58~63 HRC	Rockwell Hardness Tester	1Pc/Lot	FMT-HT-39	A
2.	ECD at 513 HV1 On PCD	*	0.75~1.15 mm	Micro Vicker / Vicker Hardness Tester	1Pc/Lot	FMT-HT-39	A
3.	Core Hardness at RCD	*	24~43 HRC	Rockwell Hardness Tester	1Pc/Lot	FMT-HT-39	A
4.	Micro Case	*	Tempered Martensite + RA (10~30)%(In 1st 0.40 mm Case Hardening Depth, Banitic Structure Are Not Allowed)	Microscope	1Pc/Lot	FMT-HT-39	A
5.	Micro Core	*	LCM+Bainitic Structure	Microscope	1Pc/Lot	FMT-HT-39	A
6.	Surface Carbon Content	*	0.80~0.95%	Microscope	1Pc/Lot	FMT-HT-39	A
7.	IGO	*	35μ-metres	Microscope	1Pc/Lot	FMT-HT-39	A

Space For Sketch:

Material- 16MnCr5

ECD Checking Pattern Details



Reaction Plan: A-यदि Inspection करते समय कम्पोनेंट खराब मिले तो खराब कम्पोनेंट को Rejection का टैग लगाकर Rejection टेबल पर रखें और उसके बारे में Department के Incharge को बतायें ।

Legends: ☒ Special Characteristics as Per Drawing * Special Characteristics For Process ☒ Special Characteristics For Safety

Change Details

Date	Rev. No.	Change	Reason for Change	Date	Rev. No.	Change	Reason for Change