





INSPECTION STANDARD (HT LAB)

☐ Prototype	☒ Pre-Launch	☐ Production	Date (Original)	19/01/2019			
Part Name:- SPUR GEAR 3RD		Part No.:- 93654746		Inspection Standard Number		SIP/4278/190	
Customer:- TMTL		Change Level.:-00		Part Stage		HT Lab.	
Sr.No.	Parameter	Special Char. Class	Methods				Reaction Plan
			Product Specification	Inspection Method	Inspection Frequency	Control Method	
1.	Surface Hardness	*	58~62 HRC	Rockwell Hardness Tester	1Pc/Lot	FMT-HT-39	A
2.	ECD Measured To 550HV	*	0.70~1.0 mm	Vicker Hardness Tester	1Pc/Lot	FMT-HT-39	A
3.	Core Hardness at PCD	*	42 HRC Max.	Rockwell Hardness Tester	1Pc/Lot	FMT-HT-39	A
4.	Core Hardness at RCD	*	30 HRC Min.	Rockwell Hardness Tester	1Pc/Lot	FMT-HT-39	A
5.	Micro Case	*	Tempered Martensite+ RA<12%, Carbide (Globular) upto 2% Max.	Microscope	1Pc/Lot	FMT-HT-39	A
6.	Core Micro	*	LCM+Bainitic Structure, Ferrite upto 5% Max.	Microscope	1Pc/Lot	FMT-HT-39	A
7.	IGO/NMTP	*	20 Micron Max.	Microscope	1Pc/Lot	FMT-HT-39	A

OPEN SKTCH

Material- 20MnCr5

Reaction Plan: A-यदि Inspection करते समय कम्पानेंट खराब मिले तो खराब कम्पानेंट को Rejection का टैग लगाकर Rejection टेबल पर रखें और उसके बारे में Department के Incharge को बतायें।

Legends: Special Characteristics as Per Drawing * Special Characteristics For Process Special Characteristics For Safety

Change Details

Date	Rev. No.	Change	Reason for Change	Date	Rev. No.	Change	Reason for Change