






INSPECTION STANDARD (HT LAB)

☐ Prototype	☒ Pre-Launch	☐ Production	Date (Original)	17/07/2020			
Part Name:-OUTPUT GEAR 4WD		Part No.:- 93641879/P		Inspection Standard Number		SIP/4373/160	
Customer :- TMTL		Change Level.:-00		Part Stage		HT Lab.	
Sr.No.	Parameter	Special Char. Class	Methods				Reaction Plan
			Product Specification	Inspection Method	Inspection Frequency	Control Method	
1.	Surface Hardness	*	58-62 HRC	Rockwell Hardness Tester	1Pc/Lot	HT Lab Report	A
2.	ECD Measured To 550HV	*	0.80~1.1 mm	Vicker / Micro Vicker Hardness Tester	1Pc/Lot	HT Lab Report	A
3.	Core Hardness at RCD	*	30HRC Min.	Rockwell Hardness Tester	1Pc/Lot	HT Lab Report	A
4.	Core Hardness at PCD	*	42 HRC Max.	Rockwell Hardness Tester	1Pc/Lot	HT Lab Report	A
5.	Micro Case	*	Tempered Martensite + RA<10%, Carbide (Globular) Upto 2% Max.	Microscope	1Pc/Lot	HT Lab Report	A
6.	Core Micro	*	LCM+Bainitic Structure, Ferrite Upto 5% Max.	Microscope	1Pc/Lot	HT Lab Report	A
7.	IGO / NMTP	*	20 Micron Max.	Microscope	1Pc/Lot	HT Lab Report	A

OPEN SKTCH

Material- 20MnCr5

Reaction Plan: A-यदि Inspection करते समय कम्पोनेंट खराब मिले तो खराब कम्पोनेंट को Rejection का टैग लगाकर Rejection टेबल पर रखें और उसके बारे में Department के Incharge को बतायें ।

Legends: ☒ Special Characteristics as Per Drawing ☒ * Special Characteristics For Process ☒ Special Characteristics For Safety

Change Details

Date	Rev. No.	Change	Reason for Change	Date	Rev. No.	Change	Reason for Change

Prepared By:

Checked By:

Approved By: