

# AHMEDABAD TEXTILE INDUSTRY'S RESEARCH ASSOCIATION



Cert. No. TC-5097

P.O. Ambawadi Vistar, Ahmedabad-380 015, India.

Ph. : (079) 26307921-7922-7923-5131-32-33 (Extn. No. : 346) Fax : (079) 26304677

E-mail : [tti@atira.in](mailto:tti@atira.in) Website : [www.atira.in](http://www.atira.in)



## TEXTILE TESTING LABORATORY ISO/IEC 17025 : 2017 NABL ACCREDITED

(Linked to Ministry of Textile)

અહમદાબાદ વસ્ત્ર ઉદ્યોગ અનુસંધાન સંસ્થાન

પી. ઓ. આંબાવાડી વિસ્તાર, અહમદાબાદ-380 015. ભારત.

### TEST REPORT

Format No.: TT 10/01/00

ULR NUMBER TC 5097 21 2 00005462F	
Test Report No: A/T/0947 2021-22	Date: 29.09.2021
Mill/Company/Customer:	Nirvana Tex Mills
Address & Contact Details:	290 Malliya, New Cloth Market Sarangpur, Ahmedabad-380002 Email : <a href="mailto:nirvanatexmills@gmail.com">nirvanatexmills@gmail.com</a>
Sample forwarding Letter No. & Date:	Nil dated Nil
Date of receipt of Sample:	27.09.2021
Lab Sample Code No. :	TT - 3319
Number of Samples : 01	
Date of Performance of test(s): 28.09.2021 to 29.09.2021	
Samples Description : Sample Design No "Amrit Zaure +SharpEN - Aqua Blue	

#### Discipline / Group : Chemical Testing / Textiles

Sr. No.	Test Parameters	Unit	Test Method	Test Results
1	Dimensional Stability Warp Weft	%	AATCC 135 @ 40° C Single Wash	-3.66 -1.19
2	Colour Fastness to Water Change in colour Staining on adjacent Polyester/Cotton/Wool Nylon/Acrylic/Acetate	Rating	ISO 105 E01	4-5 4-5/4/4 4/4-5/4-5



Page 1 of 1

★★ ISO : 17025 Accredited Laboratories ★★

AUTHORISED SIGNATORY  
Textile Testing Laboratory  
ATIRA, Ahmedabad

Samples are not drawn by ATIRA. Result relates to the samples tested. The report shall not be reproduced except in full, without written approval of the laboratory. The report is strictly confidential and for technical information of client only. Not for Advertisement, Promotion, Publicity or Litigation, Please write Test Report number and date for all future correspondence.

#### Grey Scale Rating

5. Excellent 4. Good  
3. Fair 2. Poor  
1. Very Poor

#### Pilling Rating

5. No Pilling 4. Slight Pilling  
3. Moderate Pilling 2. Severe Pilling  
1. Very Severe Pilling

Sample conditioned and tested at temp. of 27±2° (instead of 20/21±2/1° C) and 65±2% RH wherever ISO / ASTM / AATCC test methods adopted

GOOD BUSINESS ARE MEMBERS OF ATIRA : ATIRA MEMBERSHIP IS GOOD BUSINESS